

(19) World Intellectual Property  
Organization  
International Bureau




(43) International Publication Date  
24 November 2005 (24.11.2005)

PCT

(10) International Publication Number  
**WO 2005/110362 A1**

- (51) International Patent Classification<sup>7</sup>: **A61K 9/00**, 31/57, A61P 27/02
- (21) International Application Number: PCT/US2005/013143
- (22) International Filing Date: 18 April 2005 (18.04.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 10/837,355 30 April 2004 (30.04.2004) US
- (71) Applicant (for all designated States except US): **ALLERGAN, INC.** [US/US]; 2525 Dupont Drive, Irvine, CA 92612 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **NIVAGGIOLI, Thierry** [US/US]; 12020 Green Hills Court, Los Altos, CA 94022 (US). **SHIAH, Jane, Guo** [—/US]; 16 Lucero West, Irvine, CA 92620 (US). **LIN, Qing** [US/US]; 517 Briarton Terrace, Fremont, CA 94536 (US).
- (74) Agents: **DONOVAN, Stephen** et al.; Allergan Inc., 2525 Dupont Drive, Irvine, CA 92612 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: BIODEGRADABLE OCULAR IMPLANTS WITH LONG-TERM RELEASE CHARACTERISTICS



(57) Abstract: Biodegradable implants sized and suitable for implantation in an ocular region or site and methods for treating ocular conditions. The implants provide an extended release of an active agent at a therapeutically effective amount for a period of time between 30 days and one year, or longer.

WO 2005/110362 A1

## BIODEGRADABLE OCULAR IMPLANTS WITH LONG-TERM RELEASE CHARACTERISTICS

by

Thierry Nivaggioli, Jane Guo Shiah and Qing Lin

5

BACKGROUND

This invention relates to implants and methods for treating an ocular condition. In particular the present invention relates to implants and methods for treating an ocular condition by implanting into an ocular region or site an extended release bioerodible implant comprising an active agent and a bioerodible polymer. The bioerodible implants of this invention have varying and extended release rates to provide for improved kinetics of release of one or more active (therapeutic) agents over time.

15 An ocular condition can include a disease, ailment or condition which affects or involves the eye or one of the parts or regions of the eye. Broadly speaking the eye includes the eyeball and the tissues and fluids which constitute the eyeball, the periocular muscles (such as the oblique and rectus muscles) and the portion of the optic nerve which is within or adjacent to the eyeball. An anterior ocular condition is a disease, 20 ailment or condition which affects or which involves an anterior (i.e. front of the eye) ocular region or site, such as a periocular muscle, an eye lid or an eye ball tissue or fluid which is located anterior to the posterior wall of the lens capsule or ciliary muscles. Thus, an anterior ocular condition 25 primarily affects or involves, the conjunctiva, the cornea, the conjunctiva, the anterior chamber, the iris, the posterior chamber (behind the retina but in front of the posterior wall of the lens capsule), the lens or the lens capsule and blood vessels and nerve which vascularize or innervate an anterior ocular region or site. A posterior ocular condition is a disease, 30 ailment or condition which primarily affects or involves a posterior ocular region or site such as choroid or sclera (in a position posterior to a plane through the posterior wall of the lens capsule), vitreous, vitreous

chamber, retina, optic nerve (i.e. the optic disc), and blood vessels and nerves which vascularize or innervate a posterior ocular region or site.

Thus, a posterior ocular condition can include a disease, ailment or  
5 condition, such as for example, macular degeneration (such as non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (such as cystoid macular edema and diabetic macular edema); Behcet's disease, retinal disorders, diabetic  
10 retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; ocular trauma which affects a posterior ocular site or location; a posterior ocular condition caused by or influenced by an ocular laser treatment; posterior ocular conditions caused by or  
15 influenced by a photodynamic therapy; photocoagulation; radiation retinopathy; epiretinal membrane disorders; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. Glaucoma can be considered a posterior ocular condition because the therapeutic goal  
20 is to prevent the loss of or reduce the occurrence of loss of vision due to damage to or loss of retinal cells or optic nerve cells (i.e. neuroprotection).

An anterior ocular condition can include a disease, ailment or  
25 condition, such as for example, aphakia; pseudophakia; astigmatism; blepharospasm; cataract; conjunctival diseases; conjunctivitis; corneal diseases; corneal ulcer; dry eye syndromes; eyelid diseases; lacrimal apparatus diseases; lacrimal duct obstruction; myopia; presbyopia; pupil disorders; refractive disorders and strabismus. Glaucoma can also be  
30 considered to be an anterior ocular condition because a clinical goal of glaucoma treatment can be to reduce a hypertension of aqueous fluid in the anterior chamber of the eye (i.e. reduce intraocular pressure)..

The present invention is concerned with and directed to an extended release implant and methods for the treatment of an ocular condition, such as an anterior ocular condition or a posterior ocular condition or to  
5 an ocular condition which can be characterized as both an anterior ocular condition and a posterior ocular condition.

Therapeutic compounds useful for the treatment of an ocular condition can include active agents with, for example, an anti-neoplastic,  
10 anti-angiogenesis, kinase inhibition, anticholinergic, anti-adrenergic and/or anti-inflammatory activity.

Macular degeneration, such as age related macular degeneration ("AMD") is the leading cause of blindness in the world. It is estimated  
15 that thirteen million Americans have evidence of macular degeneration. Macular degeneration results in a break down the macula, the light-sensitive part of the retina responsible for the sharp, direct vision needed to read or drive. Central vision is especially affected. Macular degeneration is diagnosed as either dry (atrophic) or wet (exudative).  
20 The dry form of macular degeneration is more common than the wet form of macular degeneration, with about 90% of AMD patients being diagnosed with dry AMD. The wet form of the disease usually leads to more serious vision loss. Macular degeneration can produce a slow or sudden painless loss of vision. The cause of macular degeneration is  
25 not clear. The dry form of AMD may result from the aging and thinning of macular tissues, depositing of pigment in the macula, or a combination of the two processes. With wet AMD, new blood vessels grow beneath the retina and leak blood and fluid. This leakage causes retinal cells to die and creates blind spots in central vision.

30 Macular edema ("ME") can result in a swelling of the macula. The edema is caused by fluid leaking from retinal blood vessels. Blood leaks out of the weak vessel walls into a very small area of the macula which

is rich in cones, the nerve endings that detect color and from which daytime vision depends. Blurring then occurs in the middle or just to the side of the central visual field. Visual loss can progress over a period of months. Retinal blood vessel obstruction, eye inflammation, and age-related macular degeneration have all been associated with macular edema. The macula may also be affected by swelling following cataract extraction. Symptoms of ME include blurred central vision, distorted vision, vision tinted pink and light sensitivity. Causes of ME can include retinal vein occlusion, macular degeneration, diabetic macular leakage, eye inflammation, idiopathic central serous chorioretinopathy, anterior or posterior uveitis, pars planitis, retinitis pigmentosa, radiation retinopathy, posterior vitreous detachment, epiretinal membrane formation, idiopathic juxtafoveal retinal telangiectasia, Nd:YAG capsulotomy or iridotomy. Some patients with ME may have a history of use of topical epinephrine or prostaglandin analogs for glaucoma. The first line of treatment for ME is typically anti-inflammatory drops topically applied.

An anti-inflammatory (i.e. immunosuppressive) agent can be used for the treatment of an ocular condition, such as a posterior ocular condition, which involves inflammation, such as an uveitis or macula edema. Thus, topical or oral glucocorticoids have been used to treat uveitis. A major problem with topical and oral drug administration is the inability of the drug to achieve an adequate (i.e. therapeutic) intraocular concentration. See e.g. Bloch-Michel E. (1992). *Opening address: intermediate uveitis*, In *Intermediate Uveitis*, Dev. Ophthalmol, W.R.F. Böke et al. editors., Basel: Karger, 23:1-2; Pinar, V., et al. (1997). *Intraocular inflammation and uveitis*" In *Basic and Clinical Science Course. Section 9 (1997-1998)* San Francisco: American Academy of Ophthalmology, pp. 57-80, 102-103, 152-156; Böke, W. (1992). *Clinical picture of intermediate uveitis*, In *Intermediate Uveitis*, Dev. Ophthalmol. W.R.F. Böke et al. editors., Basel: Karger, 23:20-7; and Cheng C-K et al. (1995). *Intravitreal sustained-release dexamethasone device in the*

*treatment of experimental uveitis*, Invest. Ophthalmol. Vis. Sci. 36:442-53.

5        Systemic glucocorticoid administration can be used alone or in addition to topical glucocorticoids for the treatment of uveitis. However, prolonged exposure to high plasma concentrations (administration of 1 mg/kg/day for 2-3 weeks) of steroid is often necessary so that therapeutic levels can be achieved in the eye.

10       Unfortunately, these high drug plasma levels commonly lead to systemic side effects such as hypertension, hyperglycemia, increased susceptibility to infection, peptic ulcers, psychosis, and other complications. Cheng C-K et al. (1995). *Intravitreal sustained-release dexamethasone device in the treatment of experimental uveitis*, Invest. Ophthalmol. Vis. Sci. 36:442-53; Schwartz, B. (1966). *The response of ocular pressure to corticosteroids*, Ophthalmol. Clin. North Am. 6:929-89; Skalka, H.W. et al. (1980). *Effect of corticosteroids on cataract formation*, Arch Ophthalmol 98:1773-7; and Renfro, L. et al. (1992). *Ocular effects of topical and systemic steroids*, Dermatologic Clinics 20 10:505-12.

      Additionally, delivery to the eye of a therapeutic amount of an active agent can be difficult, if not impossible, for drugs with short plasma half-lives since the exposure of the drug to intraocular tissues is limited.

25       Therefore, a more efficient way of delivering a drug to treat a posterior ocular condition is to place the drug directly in the eye, such as directly into the vitreous. Maurice, D.M. (1983). *Micropharmaceutics of the eye*, Ocular Inflammation Ther. 1:97-102; Lee, V.H.L. et al. (1989). *Drug delivery to the posterior segment* Chapter 25 In Retina. T.E. Ogden and A.P. Schachar eds., St. Louis: CV Mosby, Vol. 1, pp. 483-98; and 30       Olsen, T.W. et al. (1995). *Human scleral permeability: effects of age*,

*cryotherapy, transscleral diode laser, and surgical thinning*, Invest. Ophthalmol. Vis. Sci. 36:1893-1903.

- Techniques such as intravitreal injection of a drug have shown promising results, but due to the short intraocular half-life of active agent, such as glucocorticoids (approximately 3 hours), intravitreal injections must be frequently repeated to maintain a therapeutic drug level. In turn, this repetitive process increases the potential for side effects such as retinal detachment, endophthalmitis, and cataracts.
- 5
- 10 Maurice, D.M. (1983). *Micropharmaceutics of the eye*, Ocular Inflammation Ther. 1:97-102; Olsen, T.W. et al. (1995). *Human scleral permeability: effects of age, cryotherapy, transscleral diode laser, and surgical thinning*, Invest. Ophthalmol. Vis. Sci. 36:1893-1903; and Kwak, H.W. and D'Amico, D. J. (1992). *Evaluation of the retinal toxicity and pharmacokinetics of dexamethasone after intravitreal injection*, Arch.
- 15 Ophthalmol. 110:259-66.

- Additionally, topical, systemic, and periocular glucocorticoid treatment must be monitored closely due to toxicity and the long-term side effects associated with chronic systemic drug exposure sequelae. Rao, N.A. et
- 20 al. (1997). *Intraocular inflammation and uveitis*, In Basic and Clinical Science Course. Section 9 (1997-1998) San Francisco: American Academy of Ophthalmology, pp. 57-80, 102-103, 152-156; Schwartz, B. (1966). *The response of ocular pressure to corticosteroids*, Ophthalmol
- 25 Clin North Am 6:929-89; Skalka, H.W. and Pichal, J.T. (1980). *Effect of corticosteroids on cataract formation*, Arch Ophthalmol 98:1773-7; Renfro, L and Snow, J.S. (1992). *Ocular effects of topical and systemic steroids*, Dermatologic Clinics 10:505-12; Bodor, N. et al. (1992). *A comparison of intraocular pressure elevating activity of loteprednol etabonate and dexamethasone in rabbits*, Current Eye Research
- 30 11:525-30.

U.S. Patent 6,217,895 discusses a method of administering a corticosteroid to the posterior segment of the eye, but does not disclose a bioerodible implant.

5 U.S. Patent 5,501,856 discloses controlled release pharmaceutical preparations for intraocular implants to be applied to the interior of the eye after a surgical operation for disorders in retina/vitreous body or for glaucoma.

10 U.S. Patent 5,869,079 discloses combinations of hydrophilic and hydrophobic entities in a biodegradable sustained release implant, and describes a polylactic acid polyglycolic acid (PLGA) copolymer implant comprising dexamethasone. As shown by *in vitro* testing of the drug release kinetics, the 100-120  $\mu$ g 50/50 PLGA/dexamethasone implant  
15 disclosed did not show appreciable drug release until the beginning of the fourth week, unless a release enhancer, such as HPMC was added to the formulation.

U.S. Patent No. 5,824,072 discloses implants for introduction into a  
20 suprachoroidal space or an avascular region of the eye, and describes a methylcellulose (i.e. non-biodegradable) implant comprising dexamethasone. WO 9513765 discloses implants comprising active agents for introduction into a suprachoroidal or an avascular region of an eye for therapeutic purposes.

25

U.S. Patents 4,997,652 and 5,164,188 disclose biodegradable ocular implants comprising microencapsulated drugs, and describes implanting microcapsules comprising hydrocortisone succinate into the posterior segment of the eye.

30

U.S. Patent 5,164,188 discloses encapsulated agents for introduction into the suprachoroid of the eye, and describes placing microcapsules



and plaques comprising hydrocortisone into the pars plana. U.S. Patent Nos. 5,443,505 and 5,766,242 discloses implants comprising active agents for introduction into a suprachoroidal space or an avascular region of the eye, and describes placing microcapsules and plaques  
5 comprising hydrocortisone into the pars plana.

Zhou *et al.* disclose a multiple-drug implant comprising 5-fluorouridine, triamcinolone, and human recombinant tissue plasminogen activator for intraocular management of proliferative vitreoretinopathy  
10 (PVR). Zhou, T, *et al.* (1998). *Development of a multiple-drug delivery implant for intraocular management of proliferative vitreoretinopathy*, Journal of Controlled Release 55: 281-295.

U.S. Patent 6,046,187 discusses methods and compositions for  
15 modulating local anesthetic by administering one or more glucocorticosteroid agents before, simultaneously with or after the administration of a local anesthetic at a site in a patient.

U.S. Patent 3,986,510 discusses ocular inserts having one or more  
20 inner reservoirs of a drug formulation confined within a bioerodible drug release rate controlling material of a shape adapted for insertion and retention in the "sac of the eye," which is indicated as being bounded by the surfaces of the bulbar conjunctiva of the sclera of the eyeball and the palpebral conjunctiva of the eyelid, or for placement over the corneal  
25 section of the eye.

U.S. Patent 6,369,116 discusses an implant with a release modifier inserted in a scleral flap.

30 EP 0 654256 discusses use of a scleral plug after surgery on a vitreous body, for plugging an incision.

U.S. Patent 4,863,457 discusses the use of a bioerodible implant to prevent failure of glaucoma filtration surgery by positioning the implant either in the subconjunctival region between the conjunctival membrane overlying it and the sclera beneath it or within the sclera itself within a partial thickness sclera flap.

EP 488 401 discusses intraocular implants, made of certain polylactic acids, to be applied to the interior of the eye after a surgical operation for disorders of the retina/vitreous body or for glaucoma.

EP 430539 discusses use of a bioerodible implant which is inserted in the suprachoroid.

Significantly, it is known that PLGA co-polymer formulations of a bioerodible polymer comprising an active agent typically release the active agent with a characteristic sigmoidal release profile (as viewed as time vs percent of total active agent released), that is after a relatively long initial lag period (the first release phase) when little if any active agent is released, there is a high positive slope period when most of the active agent is released (the second release phase) followed by another near horizontal (third) release phase, when the drug release reaches a plateau.

Thus, there is a need for a therapeutically effective extended release implant for the treatment of an ocular condition, such as posterior ocular condition. In particular, there is a need for effective delivery over an extended duration, for example, time periods extending up to 60 days, 90 days, 120 days, 6 months, 8 months, 12 months or more, preferably with maintenance of a therapeutic drug level at a desired posterior ocular region or site. Such extended delivery of an active agent can be advantageous to prevent recurrence of the inflammatory or other posterior ocular condition treated. It can also minimize the number of surgical interventions required by the patient over time to treat the

condition, as compared to the use of implants having shorter release profiles.

### SUMMARY

5       The present invention meets these and other needs and provides for bioerodible implants and implant systems that can continually, or substantially continually, release active agent, such as the steroidal anti-inflammatory agent dexamethasone, at levels corresponding to at least about 5 ng/ml (and up to about 100 ng/ml) of dexamethasone or  
10       dexamethasone equivalent in the vitreous humor for a period of between about 30 days to about 360 days or more to treat an ocular condition, such as a retinal disease. In certain variations, consistent release levels of at least 10 to 50 ng/ml of dexamethasone or dexamethasone  
15       equivalent are achieved. In other variations, a continuous or substantially active agent release level can be achieved *in vivo* (i.e. in the vitreous) for at least about 90 days or more, 120 days or more, 6 months or more, 8 months or more, and 12 months or more.

### Definitions

20       The following terms as used herein have the following meanings:

      "About" means approximately or nearly and in the context of a numerical value or range set forth herein means  $\pm 10\%$  of the numerical value or range recited or claimed.

25

      "Active agent" and "drug" are used interchangeably and refer to any substance used to treat an ocular condition.

      "Bioerodible polymer" means a polymer which degrades *in vivo*, and  
30       wherein erosion of the polymer over time is required to achieve the active agent release kinetics according to the present invention. Thus, hydrogels such as methylcellulose which act to release drug through polymer swelling are specifically excluded from the term "bioerodible (or

biodegradable) polymer". The words "bioerodible" and "biodegradable" are synonymous and are used interchangeably herein.

"Concentration equivalent to dexamethasone", or "dexamethasone equivalent" means a concentration of an active agent, such as a steroidal anti-inflammatory agent, necessary to have approximately the same efficacy *in vivo* as a particular dose of dexamethasone. For example, hydrocortisone is approximately twenty five fold less potent than dexamethasone, and thus a 25 mg dose of hydrocortisone would be equivalent to a 1 mg dose of dexamethasone. One of ordinary skill in the art would be able to determine the concentration equivalent to dexamethasone for a particular steroidal anti-inflammatory agent from one of several standard tests known in the art. Relative potencies of selected corticosteroids may be found, for example, in Gilman, A.G., *et al.*, eds. (1990). Goodman and Gilman's: The Pharmacological Basis of Therapeutics. 8th Edition, Pergamon Press: New York, p.1447.

"Cumulative release profile" means to the cumulative total percent of an active agent released from an implant into an ocular region or site *in vivo* over time or into a specific release medium *in vitro* over time.

"Extended" as in "extended period" or "extended release" means for a period of time greater than thirty days, preferably for at least 50 days (i.e. for a period of time from 50 days to 365 days), and most preferably for at least 60 days. An extended release can persist for a year or more.

"Glaucoma" means primary, secondary and/or congenital glaucoma. Primary glaucoma can include open angle and closed angle glaucoma. Secondary glaucoma can occur as a complication of a variety of other conditions, such as injury, inflammation, vascular disease and diabetes.

"Inflammation-mediated" in relation to an ocular condition means any condition of the eye which can benefit from treatment with an anti-inflammatory agent, and is meant to include, but is not limited to, uveitis, macular edema, acute macular degeneration, retinal detachment, ocular  
5 tumors, fungal or viral infections, multifocal choroiditis, diabetic uveitis, proliferative vitreoretinopathy (PVR), sympathetic ophthalmia, Vogt Koyanagi-Harada (VKH) syndrome, histoplasmosis, and uveal diffusion.

"Injury" or "damage" are interchangeable and refer to the cellular and  
10 morphological manifestations and symptoms resulting from an inflammatory-mediated condition, such as, for example, inflammation.

"Measured under infinite sink conditions *in vitro*," means assays to measure drug release *in vitro*, wherein the experiment is designed such  
15 that the drug concentration in the receptor medium never exceeds 5% of saturation. Examples of suitable assays may be found, for example, in USP 23; NF 18 (1995) pp. 1790-1798.

"Ocular condition" means a disease, ailment or condition which  
20 affects or involves the eye or one or the parts or regions of the eye, such as a retinal disease. The eye includes the eyeball and the tissues and fluids which constitute the eyeball, the periocular muscles (such as the oblique and rectus muscles) and the portion of the optic nerve which is within or adjacent to the eyeball.

25

"Plurality" means two or more.

"Posterior ocular condition" means a disease, ailment or condition which affects or involves a posterior ocular region or site such as choroid  
30 or sclera (in a position posterior to a plane through the posterior wall of the lens capsule), vitreous, vitreous chamber, retina, optic nerve (i.e. the optic disc), and blood vessels and nerve which vascularize or innervate a posterior ocular region or site.

"Steroidal anti-inflammatory agent" and "glucocorticoid" are used interchangeably herein, and are meant to include steroidal agents, compounds or drugs which reduce inflammation when administered at a therapeutically effective level.

"Substantially" in relation to the release profile or the release characteristic of an active agent from a bioerodible implant as in the phrase "substantially continuous rate" of the active agent release rate from the implant means, that the rate of release (i.e. amount of active agent released/unit of time) does not vary by more than 100%, and preferably does not vary by more than 50%, over the period of time selected (i.e. a number of days). "Substantially" in relation to the blending, mixing or dispersing of an active agent in a polymer, as in the phrase "substantially homogenously dispersed" means that there are no or essentially no particles (i.e. aggregations) of active agent in such a homogenous dispersal.

"Suitable for insertion (or implantation) in (or into) an ocular region or site" with regard to an implant, means an implant which has a size (dimensions) such that it can be inserted or implanted without causing excessive tissue damage and without unduly physically interfering with the existing vision of the patient into which the implant is implanted or inserted.

"Therapeutic levels" or "therapeutic amount" means an amount or a concentration of an active agent that has been locally delivered to an ocular region that is appropriate to safely treat an ocular condition so as to reduce or prevent a symptom of an ocular condition.

In one variation, the present invention provides for a drug delivery system for treating conditions of the eye that includes a plurality of

bioerodible implants, each bioerodible implant having a unique drug release profile. When co-administered together, one embodiment of this implant system can provide an extended continuous release of drug at levels corresponding to at least about 10 ng/ml vitreous of

5 dexamethasone or dexamethasone equivalent for a period of at least about 120 days. In certain variations, this implant system can include three implants, each of which is formed from a separate poly(lactide) (i.e. PLA) polymer or poly(lactide-co-glycolide) (i.e. PLGA) copolymer.

10 In other variations, bioerodible implants according to the present invention are prepared using two or more different bioerodible polymers each having different release characteristics. In one variation, a first quantity of the drug or active agent is blended with a first polymer and the resultant material is extruded and then broken into particles which

15 are then blended with an additional quantity of the drug or active agent and the same or a second polymer to form the final bioerodible implant, either by extrusion, injection molding or direct compression. The resultant implant has a release profile different than that of an implant created by initially blending the polymers together and provides for

20 continual or substantially continual release of active agent at levels corresponding to at least about 10 ng/ml of dexamethasone or dexamethasone equivalent for at least about 60 days.

In yet further variations, active agent can be separately blended with

25 first and second bioerodible polymers to form first and second drug-polymer mixtures that can be co-extruded to produce implants having first and second regions with differing release characteristics. The resultant implant has a release profile different than that of an implant created by initially blending the two polymers together and provides for

30 continual release of drug at levels corresponding to at least about 10 ng/ml of dexamethasone or dexamethasone equivalent for at least about 60 days.

Our invention encompasses a drug delivery system for treating an ocular condition, the drug delivery system can comprise: (a) at least one bioerodible implant suitable for insertion into an ocular region or site, the  
5 bioerodible implant comprising; (i) an active agent, and; (ii) a bioerodible polymer, wherein the bioerodible implant can release a therapeutic level of the active agent into the ocular region or site for a period time between about 30 days and about 1 year. Preferably, the bioerodible implant can release the therapeutic level of the active agent into the  
10 ocular region or site at a substantially continuous rate *in vivo*. More preferably, the bioerodible implant can release a therapeutic level of the active agent into the ocular region or site at a substantially continuous rate upon implantation in the vitreous for a period time between about 50 days and about 1 year. The active agent can be an anti-inflammatory  
15 agent. The bioerodible polymer can be a PLGA co-polymer.

The bioerodible implant can have a weight between about 1  $\mu$ g and about 100 mg and no dimension less than about 0.1 mm and no dimension greater than about 20 mm.

20

A drug delivery system of claim within the scope of our invention can comprise a plurality of bioerodible implants. The active agent can be substantially homogenously dispersed within the bioerodible polymer or the active agent can be associated with the bioerodible polymer in the  
25 form of particles of active agent and bioerodible polymer.

In a preferred embodiment the drug delivery system can comprise: (a) a portion of the active agent substantially homogenously dispersed within a portion of the bioerodible polymer, and; (b) a portion of the same  
30 or of a different active agent associated with a portion of same or of a different bioerodible polymer in the form of particles of active agent and the bioerodible polymer.



In a further embodiment the drug delivery system can comprise: (a) a bioerodible implant suitable for insertion into an ocular region or site, the bioerodible implant comprising; (i) an active agent, and; (ii) a bioerodible polymer, wherein the bioerodible implant can release a therapeutic level of the active agent upon insertion into a posterior ocular region or site for a period time of at least about 40 days.

Additionally, the drug delivery system can comprise: (a) a plurality of bioerodible implants implantable in a posterior ocular region or site, each implant comprising; (i) an active agent, and; (ii) a bioerodible polymer, wherein the plurality of bioerodible implants can substantially continuously release *in vivo* a therapeutic level of the active agent for a period time between about 5 days and about 1 year. This drug delivery system can comprise: (a) a first implant with a first release characteristic, and; (b) a second implant with a second release characteristic, wherein the first and second release characteristics differ. The release profile of the drug delivery system can correspond to the sum of the first and second release profiles. Notably, this drug delivery system can comprise: (a) a first implant with a first release characteristic, (b) a second implant with a second release characteristic, and; (c) a third implant with a third release characteristic. And the release profile of the drug delivery system can correspond to the sum of the first, second and third release profiles. The drug delivery system can comprise at least two different implants which have different bioerodible polymers. Thus, the drug deliver system can comprise first, second and third bioerodible implants, wherein the first implant comprises a first polymer with a first average molecular weight; the second implant comprises a second polymer with a second average molecular weight, and the third implant comprises a third polymer with a third average molecular weight.

- A particular embodiment of our invention can be a drug delivery system for treating a ocular condition comprising; (a) a plurality of bioerodible implants implantable in a posterior ocular region, each implant comprising (i) an anti-inflammatory drug, and; (ii) a bioerodible polymer, wherein the plurality of bioerodible implants can substantially continuously release the anti-inflammatory drug at a level of at least about a 10 ng/ml dexamethasone equivalent for a period of between 5 days and 1 year.
- 10 A preferred method for making an extended release bioerodible implant for treating an ocular condition can be by: (a) blending and extruding an active agent and a first bioerodible polymer to form a first solid material; (b) breaking the first solid material into particles; (c) blending and extruding (or direct compressing) the particles with the active agent with a second bioerodible polymer, to thereby form a bioerodible implant, wherein the bioerodible implant can release a therapeutic level of the active agent at a substantially continuous rate for a period time between about 50 days and about 1 year.
- 20 In another embodiment a bioerodible implant for treating a ocular condition, the bioerodible implant can be made by: (a) blending (followed by extruding, injection molding or the like) a steroidal anti-inflammatory drug and a first bioerodible polymer to form a first solid material; (b) breaking the solid material into particles; (c) blending (followed by extruding, injection molding or the like) the particles with the steroidal anti-inflammatory drug and a second bioerodible polymer to form a bioerodible implant, wherein the bioerodible implant can release a therapeutic level of the active agent at a substantially continuous rate for a period time between about 50 days and about 1 year. Such a bioerodible implant can substantially continuously release the steroidal anti-inflammatory drug at a dexamethasone equivalent level corresponding to at least 10 ng/ml for a period of at between 50 days

and one year. For example, the bioerodible implant can continuously releases the steroidal anti-inflammatory drug at a dexamethasone equivalent corresponding to at least 50 ng/ml for a period of at least about 50 days.

5

A bioerodible implant for treating a ocular condition can also be made as

(a) a dispersion comprising an active agent dispersed with a first bioerodible polymer, (b) a particle comprising the active agent and a  
10 second bioerodible polymer, wherein the particle has an active agent release characteristic which differs from the active agent release characteristic of the dispersion. Such an implant can substantially continuously release the active agent at a level corresponding to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for a period of  
15 at least about 50 days. Thus, such a bioerodible implant can substantially continuously release the active agent at a level corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

20 A preferred embodiment of our invention is a bioerodible implant for treating an inflammation-mediated condition of the eye, the implant being made by: (a) blending a first active agent and a first bioerodible polymer to thereby form a first active agent polymer mixture or matrix; (b) blending a second active agent and a second bioerodible polymer to  
25 thereby form a second active agent polymer mixture or matrix; (c) co-extruding the first and second active agent polymer matrixes to thereby form a bioerodible implant containing first and second regions, the first region containing the first active agent polymer matrix, and the second region containing the second active agent polymer matrix, wherein first  
30 and second regions have different active agent release characteristics. The first active agent and the second active agent can be the same active agent or the first active agent and the second active agent can be

different active agents. As well, the first polymer and the second polymer can be the same polymer or the first polymer and the second polymer can be different polymers. The implant can substantially continuously releases active agent at levels corresponding to at least 10  
5 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days. Thus, the implant can substantially continuously releases active agent at levels corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

10

A bioerodible implant for treating a posterior ocular condition can be made by: (a) blending a first active agent and a first bioerodible polymer to thereby form a first active agent polymer mixture; (b) co-extruding the first active agent polymer mixture with a second polymer to thereby form  
15 a bioerodible implant containing first and second regions, the first region containing the first active agent polymer mixture, and the second region containing the second polymer mixture.

A bioerodible implant for treating a posterior ocular condition can  
20 comprising: (a) a first region containing a first mixture of an active agent and a first bioerodible polymer, and; (b) a second region containing a second mixture of the active agent and a second bioerodible polymer, wherein the first and second regions have different active agent release characteristics. This implant can substantially continuously releases  
25 active agent at levels corresponding to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days. Alternately, this implant of can substantially continuously releases active agent at levels corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least  
30 about 50 days.

A method for treating an ocular condition according to our invention can comprise implanting into an ocular region or site a drug delivery system set forth herein.

5

### DRAWINGS

Figure 1 is a graph which shows *in vitro* cumulative release of dexamethasone (as a percent of the total amount of dexamethasone loaded into the implants) as a function of time, for the three implant  
10 system (total of 1500  $\mu$ g of dexamethasone) of Examples 1 and 2.

Figure 1B is a graph which shows the same *in vitro* cumulative release of dexamethasone shown by Figure 1, and shows as well the *in vitro* cumulative release of dexamethasone from each of the three  
15 separate (control) polymers.

Figure 2 is a graph which shows in a comparative fashion *in vivo* dexamethasone concentration (as nanograms of dexamethasone per milliliter of vitreous fluid) as a function of time, for: (a) a single 350  $\mu$ g  
20 dexamethasone implant; (b) a single 700  $\mu$ g dexamethasone implant, and; (c) the three implant system of Example 1 and 3.

Figure 3 is a graph which shows *in vitro* cumulative release of dexamethasone (as a percent of the total amount of dexamethasone loaded into each implant) as a function of time, for the multiple polymer,  
25 single implant systems of Examples 4 and 5.

Figure 4 is a graph which shows *in vitro* cumulative release of dexamethasone (as a percent of the total amount of dexamethasone loaded into each implant) as a function of time, for additional  
30 embodiments of the multiple polymer, single implant system of Examples 4 and 5.

Figure 5 is a graph which shows in a comparative fashion *in vivo* dexamethasone concentration (as nanograms of dexamethasone per milliliter of vitreous fluid) as a function of time, for: (a) an single polymer (RG755) 3 mg implant loaded with 1500  $\mu$ g of dexamethasone; (b) a particular multiple polymer (R203 island and RG502H sea) 3 mg made according to the method of Example 4 loaded with 1500  $\mu$ g of dexamethasone; (c) an single polymer 0.5 mg implant loaded with 350  $\mu$ g of dexamethasone, and; (d) an single polymer 1 mg implant loaded with 700  $\mu$ g of dexamethasone.

10

### DESCRIPTION

The present invention is based upon the discovery of bioerodible implants which can release a therapeutic amount of an active agent for an extended period of time to treat a posterior ocular condition. The present invention encompasses biodegradable ocular implants and implant systems and methods of using such implants and implant systems for treating posterior ocular conditions. The implants can be formed to be monolithic, that is the active agent is homogenously distributed or dispersed throughout the biodegradable polymer matrix. Additionally, the implants can are formed to release an active agent into an ocular region of the eye over various extended release time periods. Thus, the active agent can be released from implants made according to the present invention for an extended periods of time of approximately 60 days or more, 90 days or more, 120 days or more, 6 months or more, 8 months or more or 12 months or more.

#### Biodegradable Implants for Treating an Ocular Condition

The implants of the present invention can include an active agent mixed with or dispersed within a biodegradable polymer. The implant compositions can vary according to the preferred drug release profile, the particular active agent used, the ocular condition being treated, and

the medical history of the patient. Active agents that may be used include, but are not limited to (either by itself in an implant within the scope of the present invention or in combination with another active agent): ace-inhibitors, endogenous cytokines, agents that influence

5 basement membrane, agents that influence the growth of endothelial cells, adrenergic agonists or blockers, cholinergic agonists or blockers, aldose reductase inhibitors, analgesics, anesthetics, antiallergics, anti-inflammatory agents, antihypertensives, pressors, antibacterials, antivirals, antifungals, antiprotozoals, anti-infectives, antitumor agents,

10 antimetabolites, antiangiogenic agents, tyrosine kinase inhibitors, antibiotics such as aminoglycosides such as gentamycin, kanamycin, neomycin, and vancomycin; amphenicols such as chloramphenicol; cephalosporins, such as cefazolin HCl; penicillins such as ampicillin, penicillin, carbenicillin, oxycillin, methicillin; lincosamides such as

15 lincomycin; polypeptide antibiotics such as polymixin and bacitracin; tetracyclines such as tetracycline; quinolones such as ciproflaxin, etc.; sulfonamides such as chloramine T; and sulfones such as sulfanilic acid as the hydrophilic entity, anti-viral drugs, e.g. acyclovir, gancyclovir, vidarabine, azidothymidine, dideoxyinosine, dideoxycytosine,

20 dexamethasone , ciproflaxin, water soluble antibiotics, such as acyclovir, gancyclovir, vidarabine, azidothymidine, dideoxyinosine, dideoxycytosine; epinephrine; isoflurphate; adriamycin; bleomycin; mitomycin; ara-C; actinomycin D; scopolamine; and the like, analgesics, such as codeine, morphine, keterolac, naproxen, etc., an anesthetic,

25 e.g. lidocaine; .beta.-adrenergic blocker or .beta.-adrenergic agonist, e.g. ephidrine, epinephrine, etc.; aldose reductase inhibitor, e.g. epalrestat, ponalrestat, sorbinil, tolrestat; antiallergic, e.g. cromolyn, beclomethasone, dexamethasone, and flunisolide; colchicine, anihelminthic agents, e.g. ivermectin and suramin sodium; antiamebic

30 agents, e.g. chloroquine and chlortetracycline; and antifungal agents, e.g. amphotericin, etc., anti-angiogenesis compounds such as anecortave acetate, retinoids such as Tazarotene, anti-glaucoma

agents, such as brimonidine (Alphagan and Alphagan P), acetazolamide, bimatoprost (Lumigan), timolol, mebefunolol; memantine; alpha-2 adrenergic receptor agonists; 2-methoxyestradiol; anti-neoplastics, such as vinblastine, vincristine, interferons; alpha, beta and gamma., antimetabolites, such as folic acid analogs, purine analogs, and pyrimidine analogs; immunosuppressants such as azathioprine, cyclosporine and mizoribine; mitotic agents, such as carbachol, mydriatic agents such as atropine, etc., protease inhibitors such as aprotinin, camostat, gabexate, vasodilators such as bradykinin, etc., and various growth factors, such as epidermal growth factor, basic fibroblast growth factor, nerve growth factors, and the like.

In one variation the active agent is methotrexate. In another variation, the active agent is a retinoic acid. In another variation, the active agent is an anti-inflammatory agent such as a nonsteroidal anti-inflammatory agent. Nonsteroidal anti-inflammatory agents that may be used include, but are not limited to, aspirin, diclofenac, flurbiprofen, ibuprofen, ketorolac, naproxen, and suprofen. In a further variation, the anti-inflammatory agent is a steroidal anti-inflammatory agent, such as dexamethasone.

#### Steroidal Anti-Inflammatory Agents

The steroidal anti-inflammatory agents that may be used in the ocular implants include, but are not limited to, 21-acetoxypregnenolone, alclometasone, algestone, amcinonide, beclomethasone, betamethasone, budesonide, chloroprednisone, clobetasol, clobetasone, clocortolone, cloprednol, corticosterone, cortisone, cortivazol, deflazacort, desonide, desoximetasone, dexamethasone, diflorasone, diflucortolone, difluprednate, enoxolone, fluazacort, flucoronide, flumethasone, flunisolide, fluocinolone acetonide, fluocinonide, fluocortin butyl, fluocortolone, fluorometholone, fluperolone acetate, fluprednidene acetate, fluprednisolone, flurandrenolide, fluticasone propionate,



formocortol, halcinonide, halobetasol propionate, halometasone, halopredone acetate, hydrocortamate, hydrocortisone, loteprednol etabonate, mazipredone, medrysone, meprednisone, methylprednisolone, mometasone furoate, paramethasone, prednicarbate, prednisolone, prednisolone 25-diethylamino-acetate, prednisolone sodium phosphate, prednisone, prednival, prednylidene, rimexolone, tixocortol, triamcinolone, triamcinolone acetonide, triamcinolone benetonide, triamcinolone hexacetonide, and any of their derivatives.

10

In one embodiment, cortisone, dexamethasone, fluocinolone, hydrocortisone, methylprednisolone, prednisolone, prednisone, and triamcinolone, and their derivatives, are preferred steroidal anti-inflammatory agents. In another preferred variation, the steroidal anti-inflammatory agent is dexamethasone. In another variation, the biodegradable implant includes a combination of two or more steroidal anti-inflammatory agents.

15

The active agent, such as a steroidal anti-inflammatory agent, can comprise from about 10% to about 90% by weight of the implant. In one variation, the agent is from about 40% to about 80% by weight of the implant. In a preferred variation, the agent comprises about 60% by weight of the implant. In a more preferred embodiment of the present invention, the agent can comprise about 50% by weight of the implant.

25

#### Biodegradable Polymers

In one variation, the active agent can be homogeneously dispersed in the biodegradable polymer of the implant. The implant can be made, for example, by a sequential or double extrusion method. The selection of the biodegradable polymer used can vary with the desired release kinetics, patient tolerance, the nature of the disease to be treated, and the like. Polymer characteristics that are considered include, but are not

30

limited to, the biocompatibility and biodegradability at the site of implantation, compatibility with the active agent of interest, and processing temperatures. The biodegradable polymer matrix usually comprises at least about 10, at least about 20, at least about 30, at least about 40, at least about 50, at least about 60, at least about 70, at least about 80, or at least about 90 weight percent of the implant. In one variation, the biodegradable polymer matrix comprises about 40% to 50% by weight of the implant.

Biodegradable polymers which can be used include, but are not limited to, polymers made of monomers such as organic esters or ethers, which when degraded result in physiologically acceptable degradation products. Anhydrides, amides, orthoesters, or the like, by themselves or in combination with other monomers, may also be used. The polymers are generally condensation polymers. The polymers can be crosslinked or non-crosslinked. If crosslinked, they are usually not more than lightly crosslinked, and are less than 5% crosslinked, usually less than 1% crosslinked.

For the most part, besides carbon and hydrogen, the polymers will include oxygen and nitrogen, particularly oxygen. The oxygen may be present as oxy, e.g., hydroxy or ether, carbonyl, e.g., non-oxo-carbonyl, such as carboxylic acid ester, and the like. The nitrogen can be present as amide, cyano, and amino. An exemplary list of biodegradable polymers that can be used are described in Heller, Biodegradable Polymers in Controlled Drug Delivery, In: "CRC Critical Reviews in Therapeutic Drug Carrier Systems", Vol. 1. CRC Press, Boca Raton, FL (1987).

Of particular interest are polymers of hydroxyaliphatic carboxylic acids, either homo- or copolymers, and polysaccharides. Included among the polyesters of interest are homo- or copolymers of D-lactic

acid, L-lactic acid, racemic lactic acid, glycolic acid, caprolactone, and combinations thereof. Copolymers of glycolic and lactic acid are of particular interest, where the rate of biodegradation is controlled by the ratio of glycolic to lactic acid. The percent of each monomer in  
5 poly(lactic-co-glycolic)acid (PLGA) copolymer may be 0-100%, about 15-85%, about 25-75%, or about 35-65%. In certain variations, 25/75 PLGA and/or 50/50 PLGA copolymers are used. In other variations, PLGA copolymers are used in conjunction with polylactide polymers.

10 Biodegradable polymer matrices that include mixtures of hydrophilic and hydrophobic ended PLGA may also be employed, and are useful in modulating polymer matrix degradation rates. Hydrophobic ended (also referred to as capped or end-capped) PLGA has an ester linkage hydrophobic in nature at the polymer terminus. Typical hydrophobic end  
15 groups include, but are not limited to alkyl esters and aromatic esters. Hydrophilic ended (also referred to as uncapped) PLGA has an end group hydrophilic in nature at the polymer terminus. PLGA with a hydrophilic end groups at the polymer terminus degrades faster than hydrophobic ended PLGA because it takes up water and undergoes  
20 hydrolysis at a faster rate (Tracy et al., *Biomaterials* 20:1057-1062 (1999)). Examples of suitable hydrophilic end groups that may be incorporated to enhance hydrolysis include, but are not limited to, carboxyl, hydroxyl, and polyethylene glycol. The specific end group will typically result from the initiator employed in the polymerization process.  
25 For example, if the initiator is water or carboxylic acid, the resulting end groups will be carboxyl and hydroxyl. Similarly, if the initiator is a monofunctional alcohol, the resulting end groups will be ester or hydroxyl.

### 30 Additional Agents

Other agents may be employed in the formulation for a variety of purposes. For example, buffering agents and preservatives may be

employed. Preservatives which may be used include, but are not limited to, sodium bisulfite, sodium bisulfate, sodium thiosulfate, benzalkonium chloride, chlorobutanol, thimerosal, phenylmercuric acetate, phenylmercuric nitrate, methylparaben, polyvinyl alcohol and phenylethyl alcohol. Examples of buffering agents that may be employed include, but are not limited to, sodium carbonate, sodium borate, sodium phosphate, sodium acetate, sodium bicarbonate, and the like, as approved by the FDA for the desired route of administration. Electrolytes such as sodium chloride and potassium chloride may also be included in the formulation.

The biodegradable ocular implants can also include additional hydrophilic or hydrophobic compounds that accelerate or retard release of the active agent. Additionally, release modulators such as those described in U.S. Patent No. 5,869,079 can be included in the implants. The amount of release modulator employed will be dependent on the desired release profile, the activity of the modulator, and on the release profile of the glucocorticoid in the absence of modulator. Where the buffering agent or release enhancer or modulator is hydrophilic, it may also act as a release accelerator. Hydrophilic additives act to increase the release rates through faster dissolution of the material surrounding the drug particles, which increases the surface area of the drug exposed, thereby increasing the rate of drug diffusion. Similarly, a hydrophobic buffering agent or enhancer or modulator can dissolve more slowly, slowing the exposure of drug particles, and thereby slowing the rate of drug diffusion.

#### Release Kinetics

An implant within the scope of the present invention can be formulated with particles of an active agent dispersed within a biodegradable polymer matrix. Without being bound by theory, it is believed that the release of the active agent can be achieved by erosion

of the biodegradable polymer matrix and by diffusion of the particulate agent into an ocular fluid, e.g., the vitreous, with subsequent dissolution of the polymer matrix and release of the active agent. Factors which influence the release kinetics of active agent from the implant can include such characteristics as the size and shape of the implant, the size of the active agent particles, the solubility of the active agent, the ratio of active agent to polymer(s), the method of manufacture, the surface area exposed, and the erosion rate of the polymer(s). The release kinetics achieved by this form of active agent release are different than that achieved through formulations which release active agents through polymer swelling, such as with crosslinked hydrogels. In that case, the active agent is not released through polymer erosion, but through polymer swelling and drug diffusion, which releases agent as liquid diffuses through the pathways exposed.

15

The release rate of the active agent can depend at least in part on the rate of degradation of the polymer backbone component or components making up the biodegradable polymer matrix. For example, condensation polymers may be degraded by hydrolysis (among other mechanisms) and therefore any change in the composition of the implant that enhances water uptake by the implant will likely increase the rate of hydrolysis, thereby increasing the rate of polymer degradation and erosion, and thus increasing the rate of active agent release.

25

The release kinetics of the implants of the present invention can be dependent in part on the surface area of the implants. A larger surface area exposes more polymer and active agent to ocular fluid, causing faster erosion of the polymer matrix and dissolution of the active agent particles in the fluid. Therefore, the size and shape of the implant may also be used to control the rate of release, period of treatment, and active agent concentration at the site of implantation. At equal active agent loads, larger implants will deliver a proportionately larger dose, but

30

depending on the surface to mass ratio, may possess a slower release rate. For implantation in an ocular region, the total weight of the implant preferably ranges, e.g., from about 100  $\mu\text{g}$  to about 15 mg. More preferably, from about 300  $\mu\text{g}$  to about 10 mg, and most preferably from  
5 about 500  $\mu\text{g}$  to about 5 mg. In a particularly preferred embodiment of the present invention the weight of an implant is between about 500  $\mu\text{g}$  and about 2 mg, such as between about 500  $\mu\text{g}$  and about 1 mg.

The bioerodible implants are typically solid, and may be formed as  
10 particles, sheets, patches, plaques, films, discs, fibers, rods, and the like, or may be of any size or shape compatible with the selected site of implantation, as long as the implants have the desired release kinetics and deliver an amount of active agent that is therapeutic for the intended medical condition of the eye. The upper limit for the implant size will be  
15 determined by factors such as the desired release kinetics, toleration for the implant at the site of implantation, size limitations on insertion, and ease of handling. For example, the vitreous chamber is able to accommodate relatively large rod-shaped implants, generally having diameters of about 0.05 mm to 3 mm and a length of about 0.5 to about  
20 10 mm. In one variation, the rods have diameters of about 0.1 mm to about 1 mm. In another variation, the rods have diameters of about 0.3 mm to about 0.75 mm. In yet a further variation, other implants having variable geometries but approximately similar volumes may also be used.

25

The proportions of active agent, polymer, and any other modifiers may be empirically determined by formulating several implants with varying proportions. A USP approved method for dissolution or release test can be used to measure the rate of release (USP 23; NF 18 (1995)  
30 pp. 1790-1798). For example, using the infinite sink method, a weighed sample of the drug delivery device is added to a measured volume of a solution containing 0.9% NaCl in water, where the solution volume will

be such that the drug concentration after release is less than 20%, and preferably less than 5%, of saturation. The mixture is maintained at 37°C and stirred slowly to ensure drug diffusion after bioerosion. The appearance of the dissolved drug as a function of time may be followed  
5 by various methods known in the art, such as spectrophotometrically, HPLC, mass spectroscopy, etc.

#### Applications

Examples of ocular conditions which can be treated by the implants  
10 and methods of the invention include, but are not limited to, glaucoma, uveitis, macular edema, macular degeneration, retinal detachment, posterior ocular tumors, fungal or viral infections, multifocal choroiditis, diabetic retinopathy, proliferative vitreoretinopathy (PVR), sympathetic  
15 opthalmia, Vogt Koyanagi-Harada (VKH) syndrome, histoplasmosis, uveal diffusion, and vascular occlusion. In one variation, the implants are particularly useful in treating such medical conditions as uveitis, macular edema, vascular occlusive conditions, proliferative vitreoretinopathy (PVR), and various other retinopathies.

#### Methods of Implantation

The biodegradable implants can be inserted into the eye by a variety of methods, including placement by forceps, by trocar, or by other types of applicators, after making an incision in the sclera. In some instances, a trocar or applicator may be used without creating an incision. In a  
25 preferred variation, a hand held applicator is used to insert one or more biodegradable implants into the eye. The hand held applicator typically comprises an 18-30 GA stainless steel needle, a lever, an actuator, and a plunger. Suitable devices for inserting an implant or implants into a posterior ocular region or site includes those disclosed in United States  
30 patent application serial number 10/666,872.

The method of implantation generally first involves accessing the target area within the ocular region with the needle, trocar or implantation device. Once within the target area, e.g., the vitreous cavity, a lever on a hand held device can be depressed to cause an actuator to drive a plunger forward. As the plunger moves forward, it can push the implant or implants into the target area (i.e. the vitreous).

#### Methods for Making Implants

Various techniques may be employed to make implants within the scope of the present invention. Useful techniques include phase separation methods, interfacial methods, extrusion methods, compression methods, molding methods, injection molding methods, heat press methods and the like.

Choice of the technique, and manipulation of the technique parameters employed to produce the implants can influence the release rates of the drug. Room temperature compression methods result in an implant with discrete microparticles of drug and polymer interspersed. Extrusion methods result in implants with a progressively more homogenous dispersion of the drug within a continuous polymer matrix, as the production temperature is increased.

The use of extrusion methods allows for large-scale manufacture of implants and results in implants with a homogeneous dispersion of the drug within the polymer matrix. When using extrusion methods, the polymers and active agents that are chosen are stable at temperatures required for manufacturing, usually at least about 50°C. Extrusion methods use temperatures of about 25°C to about 150°C, more preferably about 60°C to about 130°C.

Different extrusion methods may yield implants with different characteristics, including but not limited to the homogeneity of the



dispersion of the active agent within the polymer matrix. For example, using a piston extruder, a single screw extruder, and a twin screw extruder will generally produce implants with progressively more homogeneous dispersion of the active. When using one extrusion  
5 method, extrusion parameters such as temperature, extrusion speed, die geometry, and die surface finish will have an effect on the release profile of the implants produced.

In one variation of producing implants by a piston extrusion methods,  
10 the drug and polymer are first mixed at room temperature and then heated to a temperature range of about 60°C to about 150°C, more usually to about 100°C for a time period of about 0 to about 1 hour, more usually from about 0 to about 30 minutes, more usually still from about 5 minutes to about 15 minutes, and most usually for about 10 minutes.  
15 The implants are then extruded at a temperature of about 60°C to about 130°C, preferably at a temperature of about 90°C.

In an exemplary screw extrusion method, the powder blend of active agent and polymer is added to a single or twin screw extruder preset at  
20 a temperature of about 80°C to about 130°C, and directly extruded as a filament or rod with minimal residence time in the extruder. The extruded filament or rod is then cut into small implants having the loading dose of active agent appropriate to treat the medical condition of its intended use.

25

Implant systems according to the invention can include a combination of a number of bioerodible implants, each having unique polymer compositions and drug release profiles that when co-administered provide for an extended continuous release of drug. Further, the  
30 achieved continuous release of drug is both prolonged and distinct from the release profile that would occur with a single implant consisting of a blend of the polymers. For example, to achieve continuous release of

at least 120 days, three individual implants made of separate polymers that have fast, medium and slow release characteristics can be employed, with the fast release implant releasing most of the drug from 0-60 days, the medium release implant releasing most of the drug from 60-100 days, and the slow release implant releasing most of the drug from 100 days on. Examples of fast release implants include those made of certain lower molecular weight, fast degradation profile polylactide polymers, such as R104 made by Boehringer Ingelheim GmbH, Germany, which is a poly(D,L-lactide) with a molecular weight of about 3,500. Examples of medium release implants include those made of certain medium molecular weight, intermediate degradation profile PLGA co-polymers, such as RG755 made by Boehringer Ingelheim GmbH, Germany, which is a poly(D,L-lactide-co-glycolide with wt/wt 75% lactide :25% glycolide, a molecular weight of about 40,000 and an inherent viscosity of 0.50 to 0.70 dl/g. Examples of slow release implants include those made of certain other high molecular weight, slower degradation profile polylactide polymers, such as R203/RG755 made by Boehringer Ingelheim GmbH, Germany, for which the molecular weight is about 14,000 for R203 (inherent viscosity of 0.25 to 0.35 dl/g) and about 40,000 for RG755. When administered together, these implants provide for an extend continuous release of drug over a period of at least 120 days *in vitro* which can result in sustained drug levels (concentration) of at least about 5-10 ng dexamethasone equivalent/mL in the vitreous (i.e. *in vivo*) for up to about 240 days.

25

Single bioerodible implants with extended release profiles can also be prepared according to the invention using two or more different bioerodible polymers each having different release characteristics. In one such method, particles of a drug or active agent are blended with a first polymer and extruded to form a filament or rod. This filament or rod is then itself broken first into small pieces and then further ground into particles with a size (diameter) between about 30  $\mu\text{m}$  and about 50  $\mu\text{m}$ .

30

- which are then blended with an additional quantities of the drug or active agent and a second polymer. This second mixture is then extruded into filaments or rods which are then cut to the appropriate size to form the final implant. The resultant implant has a release profile different than
- 5 that of an implant created by initially blending the two polymers together and then extruding it. It is posited that formed implant includes initial particles of the drug and first polymer having certain specific release characteristics bound up in the second polymer and drug blend that itself has specific release characteristics that are distinct from the first.
- 10 Examples of implants include those formed with RG755, R203, RG503, RG502, RG 502H as the first polymer, and RG502, RG 502H as the second polymer. Other polymers that can be used include PDL (poly(D,L-lactide)) and PDLG (poly(D,L-lactide-co-glycolide)) polymers available from PURAC America, Inc. Lincolnshire, IL.
- 15 Poly(caprolactone) polymers can also be used. The characteristics of the specified polymers are (1) RG755 has a molecular weight of about 40,000, a lactide content (by weight) of 75%, and a glycolide content (by weight) of 25%; (2) R203 has a molecular weight of about 14,000, and a lactide content of 100% ; (3) RG503 has a molecular weight of about
- 20 28,000, a lactide content of 50%, and a glycolide content of 50%; (4) RG502 has a molecular weight of about 11,700 (inherent viscosity of 0.16 to 0.24 dl/g), a lactide content of 50%, and a glycolide content of 50%, and; (5) RG502H has a molecular weight of about 8,500, a lactide content of 50%, a glycolide content of 50% and free acid at the end of
- 25 polymer chain.

Generally, if inherent viscosity is 0.16 the molecular weight is about 6,300, and if the inherent viscosity is 0.28 the molecular weight is about 20,700. It is important to note that all polymer molecular weights set

30 forth herein are averaged molecular weights in Daltons.

According to our invention continual or substantially continual release of drug at levels corresponding to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for at least 60 days can be achieved.

5 In other methods, single implants can be made using polymers with differing release characteristics where separate drug-polymer blends are prepared that are then co-extruded to create implants that contain different areas or regions having different release profiles. The overall drug release profile of these co-extruded implants are different than that  
10 of an implant created by initially blending the polymers together and then extruding them. For example, first and second blends of drug or active agent can be created with different polymers and the two blends can be co-axially extruded to create an implant with an inner core region having certain release characteristics and an outer shell region having second,  
15 differing release characteristics.

### EXAMPLES

The following examples illustrate aspects and embodiments of the  
20 invention.

#### Example 1

##### Preparation of Dexamethasone Three Implant Extended Release System

25 A bioerodible implant system for extended delivery of dexamethasone was made by mixing the active agent dexamethasone (Pharmacia Corp., Peapack, NJ) separately with each of the following three different polymers:

1. poly (D,L-lactide) (R104, Boehringer Ingelheim GmbH, Germany),
  - 30 2. poly(D,L-lactide-co-glycolide) as a 75:25 (wt%/wt%) blend of lactide:glycolide (RG755, Boehringer Ingelheim GmbH, Germany), and;
  3. poly (D,L-lactide) (R203, Boehringer Ingelheim GmbH, Germany),
- so as to obtain three different dexamethasone-polymer mixes.

R203 and R104 both are poly(D,L-lactide) polymers, but with different molecular weights. The molecular weight for R203 is about 14,000, while the molecular weight for R104 is about 3,500. RG755 is a  
5 poly(lactide-co-glycolide) co-polymer. The molecular weight of RG755 is about 40,000.

The dexamethasone and one of the three polymers specified above were thoroughly mixed at a ratio of 50/50 by weight ratio of  
10 dexamethasone and each of the three polymers.

Each of the three separate batches of the three dexamethasone-polymer blends were then fed into a single-piston thermal extruder and three different extruded dexamethasone-polymer filaments were thereby  
15 made. The filaments were further processed to obtain individual segments (implants), each segment being about a 1 mg implant containing approximately 0.5 mg of dexamethasone. The three implant system consisted of one of each of the 1 mg implants for each of the three polymers (R104, RG755 or R203) which had been combined  
20 separately with 0.5 mg of dexamethasone). The total dexamethasone concentration in the combined three implants was about 1.5 mg, as of the three implants weighed about 1 mg and each of the three implants contained about 50% by weight dexamethasone. A three implant dexamethasone extended release system was thereby made.

25

#### Example 2

##### *In vitro* Release of Dexamethasone from Three Implant Extended Release System

Cumulative release of dexamethasone from the three implant system  
30 of Example 1 was measured *in vitro*. The three implant system was placed in a glass vial filled with receptor medium (0.1 M phosphate solution, pH 4.4, at 37 degrees C). To allow for "infinite sink" conditions, the receptor medium volume was chosen so that the concentration

would never exceed 5% of saturation. To minimize secondary transport phenomena, *e.g.* concentration polarization in the stagnant boundary layer, the glass vial was placed into a shaking water bath at 37°C.

Samples were taken for HPLC analysis from the vial at defined time  
5 points. The concentration values were used to calculate the cumulative release data, as shown in Table 1 and the corresponding Figure 1. In Table 1 "Day" is the day of the *in vitro* measurement of the cumulative amount of dexamethasone released from the three implants, "Cum." is an abbreviation for cumulative and "Dex" is an abbreviation for  
10 dexamethasone.

Figure 1B is a graph which shows the same *in vitro* cumulative release of dexamethasone shown by Figure 1, and shows as well the *in vitro* cumulative release of dexamethasone from each of the three  
15 separate (control) polymers release separately from each of the 1 mg implants for each of the three polymers (R104, RG755 or R203) which had been combined separately with 0.5 mg of dexamethasone. Table 1B sets forth the data for Figure 1B.

20 This experiment showed that use of the cumulative release of dexamethasone from the three implant system of Example 1 permitted *in vitro* release over a 161 day period, a substantially continuous release of the active agent at a substantially constant release rate (*i.e.* approximately linear, positive slope).

25

### Example 3

#### *In vivo* Release of Dexamethasone from Three Implant Extended Release System

30 The three implant system of Example 1 was implanted into the vitreous of the eyes of eight rabbits. This was carried out by loading the three implants of Example 1 into a simple trocar with a sample holder and plunger, making an incision through the lower front sclera, inserting

the trocar through the scleral incision, and depressing the trocar plunger to deposit the three implants of Example 1 into the vitreous. The *in vivo* vitreous concentrations of dexamethasone were monitored by vitreous sampling, using LC/MS (liquid chromatography and mass spectrometry).

5 The dexamethasone concentrations for each eye were measured at days 7, 30, 60, 90, 120, 150, 180, 210 and 240 and 360 for the three implant system of Example 1. The averaged results of one mixed concentration measurement are set forth by the two left hand side columns of Table 2.

10

Comparison studies were also carried out using single (Posurdex) implants of dexamethasone and a bioerodible PLGA polymer. Specifically, the single extruded comparison study implants were formed of dexamethasone mixed with polylactic acid-polyglycolic acid (PLGA)

15 as the biodegradable polymer at a ratio of 60/30/10 by weight of dexamethasone (60% by weight), PLGA (RG502, Boehringer Ingelheim GmbH, Germany) (10% by weight), and free acid end PLGA (RG502H, Boehringer Ingelheim GmbH, Germany) (30% by weight), respectively. Two versions of these comparison study implants were prepared; one  
20 contained 350 µg of dexamethasone and the other implant contained 700 µg of dexamethasone. These single bioerodible dexamethasone (Posurdex) implants were in the same manner used for the three implant systems implanted into the vitreous of rabbit eyes (note that only one of either the 350 µg dexamethasone or the 700 µg dexamethasone  
25 bioerodible implant was placed into each eye) and *in vivo* vitreous concentrations of dexamethasone from the 350µg and 700 µg comparison study single implants were monitored by vitreous sampling. The dexamethasone concentrations for each eye were measured at days 1, 4, 7, 14, 21, 28, 35, 42; as shown as the three right hand side  
30 columns of by Table 2.

The RG502 (molecular weight is about 11,700) and RG502H (molecular weight is about 8,500) polymers used are both poly(D,L-lactide-co-glycolide). RG502H has a free acid at the end of its polymer chain.

5

All dexamethasone measurement are as concentrations in ng dexamethasone per ml of vitreous fluid.

Figure 2 shows (using the Table 2 data) the vitreous concentrations of dexamethasone assayed after different time periods after intra-vitreous *in vivo* implantation of the implant system of Example 1 in comparison to the vitreous concentrations of dexamethasone obtained for the single intra-vitreous implantation of the 350 µg or 700 µg dexamethasone implants described above in this Example 3.

15

This experiment showed that the bioerodible implant system of Example 1 can release dexamethasone *in vivo* into the vitreous: (1) for a time period both much longer than (i.e. about 360 days vs about 30 days) and in a much more linear fashion than can a single dexamethasone agent (comparison study) implant. Significantly, this experiment showed that use of three bioerodible polymeric dexamethasone implants wherein each of the implant polymers was different permitted (as a cumulative view of the release characteristics of the three implants taken together), *in vivo* over a 360 day period, a substantially continuous release of the dexamethasone active agent at a substantially constant release rate (i.e. approximately linear release with substantially zero slope).

20

25

Additionally, this experiment showed that the bioerodible implant system of Example 1 can release and maintain an *in vivo* in the vitreous a dexamethasone (or dexamethasone equivalent) concentration of at least 10 ng/ml or of at least about 100 ng/ml for a period of time of 120

30



days or for 360 days. This experiment also showed that by comparison, the single (350 or 700  $\mu$ g) implants exhausted delivery of dexamethasone into the vitreous after about 30 days and that even during that more shorter release period the single bioerodible implant could not release or maintain an *in vivo* in the vitreous a dexamethasone (or dexamethasone equivalent) concentration with either a substantially continuous release or with a substantially constant release rate of the active agent.

10

#### Example 4

##### Preparation of Dexamethasone Extended Delivery Single Implants

A. Extended delivery implants containing dexamethasone were prepared as follows. The active agent dexamethasone was first thoroughly mixed with a selected polymer at a ratio of 60% by weight dexamethasone and 40% by weight polymer in five separate batches with each of the following five different bioerodible polymers:

1. poly (D,L-lactide) (R203, Boehringer Ingelheim GmbH, Germany),
2. poly (D,L-lactide-co-glycolide) (PLGA) at 50% lactide/%50 glycolic acid (50/50) (R502, Boehringer Ingelheim GmbH, Germany),
- 20 3. PLGA free acid end (50/50) (RG502H, Boehringer Ingelheim GmbH, Germany),
4. PLGA 50/50 (R503, Boehringer Ingelheim GmbH, Germany), and;
5. PLGA 75% lactide/25% glycolic acid (RG755, Boehringer Ingelheim GmbH, Germany)

25

B. RG755: molecular weight is about 40,000; lactide is 75% by weight and glycolide is 25% by weight.

R203: molecular weight is about 14,000, lactide=100%

RG503: molecular weight is about 28,300, lactide=50%, glycolide=50%

30 RG502: molecular weight is about 11,700, lactide=50%, glycolide=50%

RG502H: molecular weight is about 8,500, lactide=50%, glycolide=50%, free acid at the end of polymer chain

C. The dexamethasone active agent and the polymer (one of the five) were thoroughly mixed at a ratio of 60/40 (wt/wt) by weight of dexamethasone and polymer for each batch. This was carried out with  
5 each of the five polymers to obtain five different dexamethasone-polymer blends (same amount of dexamethasone in each of the five different polymer blends).

D. Each of the five separate batches of the five different 60%  
10 dexamethasone-40% polymer blends were then fed separately into an extruder and five different extruded dexamethasone-polymer filaments were collected. The filaments so obtained were then separately ground into dexamethasone-polymer particles of 30  $\mu$ m to 50  $\mu$ m in diameter. There was thereby prepared five different "islands", as explained below.

15

E. There was then separately prepared: (1) a blend of dexamethasone and RG502 polymer (as dexamethasone 40% by weight/RG502 60% by weight), and; (2) a blend of dexamethasone and RG502H polymer (as dexamethasone 40% by weight/RG502H 60% by  
20 weight). There was thereby prepared two different "seas", as explained below.

F. For each of the five batches of the dexamethasone-polymer (one of five) particles (the islands) previously obtained, the particles were  
25 then separately and thoroughly mixed with either the dexamethasone-bioerodible polymer RG502 blend or with the dexamethasone-bioerodible polymer RG502H blend (i.e. with one of the seas). The resulting (island and sea) mixture was then again fed into an extruder and the extruded dexamethasone -polymer filaments were collected and  
30 further processed to obtain individual segments, each providing a single, composite implant comprising 500  $\mu$ g of dexamethasone.

In summary, the 500  $\mu$ g dexamethasone first extruded filament (60/40 dexamethasone/polymer) was ground into particles and the particles mixed with the 500  $\mu$ g second batch (which was 40/60 dexamethasone/polymer) so the amount of dexamethasone in the final 1 mg extruded filament: was  $(500\mu\text{g} \times 60\%) + (500\mu\text{g} \times 40\%) = 500 \mu\text{g}$  dexamethasone.

G. The word "island" is used here to mean the dexamethasone-bioerodible polymer particle prepared in paragraph D. above. The word "sea" is used to describe dexamethasone dispersed (such as homogenously dispersed) within a second bioerodible polymer (i.e. not as particles or islands), as set forth by paragraph E. above.

Three control implants were also prepared. All three control implants were all sea implants (no islands). The first control implant consisted of dexamethasone dispersed within the bioerodible polymer RG502H. The second control implant consisted of dexamethasone dispersed within the bioerodible polymer RG502. The third control implant consisted of dexamethasone dispersed within the bioerodible polymer R203. All the control implants were made by extruding a single polymer and dexamethasone mixture. The three control implants were essentially Posurdex type implants. All the control group samples were prepared by 50/50% weight of dexamethasone and individual polymer, and were prepared as a 1 mg implant containing 500  $\mu$ g dexamethasone)

25

Each of these two island and sea implants and each of the three control implants contained 500  $\mu$ g of dexamethasone.

The implants set forth above in Example 4 were made as 1 mg cylindrical implants. Also made, by tripling the polymer and dexamethasone amounts set forth above, were 3 mg (1500  $\mu$ g of

30

dexamethasone) RG755 single polymer implants, and 3 mg (1500  $\mu$ g dexamethasone) R203/RG502H two polymer implants.

#### Example 5

##### 5     *In vitro* Performance of Dexamethasone Extended Delivery Single Implants

Release of dexamethasone from selected implants of Example 4 was measured *in vitro*. Control implants were also prepared and tested, the control implants made by extruding a single polymer and  
10     dexamethasone mixture. In all control groups, the samples were prepared by 50/50% weight of dexamethasone and individual polymer, and there was 500  $\mu$ g dexamethasone per each 1 mg implant. Implants were placed in glass vials filled with receptor medium (0.1 M phosphate solution, pH 4.4, at 37 degrees C). To allow for "infinite sink" conditions,  
15     the receptor medium volume was chosen so that the concentration would never exceed 5% of saturation. To minimize secondary transport phenomena, *e.g.* concentration polarization in the stagnant boundary layer, the glass vials were placed into a shaking water bath at 37°C. Samples were taken for HPLC analysis from the vials at days 1, 4, 7, 14,  
20     21, 28, 35, 42 and 49 days. Some samples were also taken on days 63 and 77. The concentration values were used to calculate the cumulative release data, as shown in Table 3 and Figures 3 and 4.

Figure 3 presents *in vitro* dexamethasone release characteristic for  
25     two implants: (1) one where the island of the implant consisted of dexamethasone-R203 polymer particles and the sea of the same implant consisted of dexamethasone dispersed in RG502H polymer, and; (2) a second implant where the island of this second implant consisted of dexamethasone-R203 polymer particles and the sea of this second  
30     implant consisted of dexamethasone dispersed in RG502 polymer material. It was observed that such island and sea implant formulations led to release profiles not predictable from the individual characteristics

of either the island or sea bioerodible polymers alone with dexamethasone.

Figure 4 presents *in vitro* dexamethasone release characteristic for two implants: (1) one where the island of the implant consisted of dexamethasone-RG755 polymer particles and the sea of the same implant consisted of dexamethasone dispersed in RG502H polymer, and; (2) a second implant where the island of this second implant consisted of dexamethasone-RG755 polymer particles and the sea of this second implant consisted of dexamethasone dispersed in RG502 polymer material. It was observed that such island and sea implant formulations led to release profiles not predictable from the individual characteristics of either the island or sea bioerodible polymers alone with dexamethasone.

15

These *in vitro* release results show that implants made from a plurality of polymers can have varying *in vitro* release profiles which permit substantially linear release of dexamethasone for up to at least about 80 days.

20

#### Example 6

##### *In vivo* Release of Dexamethasone from Extended Release Implants

Implants of Example 4 were implanted into the vitreous of separate eyes of fourteen rabbits. This was carried out by loading the implant into a trocar, making an incision through the sclera, inserting the trocar through the scleral incision, and depressing the trocar plunger to deposit separate Example 5 into the vitreous of separate eyes. The *in vivo* vitreous concentrations of dexamethasone were monitored by vitreous sampling using LC/MS. The dexamethasone concentrations for each eye were measured at days 7, 21, 35, 49, 63, 77 and 112. The averaged results of measurements are set forth by Table 4 for an RG755 polymer 3 mg (1500  $\mu$ g dexamethasone) implant and for a R203 (island)/RG502H (sea) 3 mg (1500  $\mu$ g dexamethasone) implant.

Comparison studies were also carried out using single (Posurdex) 0.5 mg or 1 mg implants of (350  $\mu$ g or 700  $\mu$ g) dexamethasone and a bioerodible polymer ("Single Polymer Implants" in Table 4). Specifically, the single extruded process implants were formed of dexamethasone mixed with polylactic acid-polyglycolic acid (PLGA) as the biodegradable polymer at a ratio of 70/30 by weight of dexamethasone (70% by weight), and PLGA (Birmingham Polymers, Inc., Birmingham, Alabama, inherent viscosity 0.16) (30% by weight). Two versions of the implants were prepared, one contained 350  $\mu$ g of dexamethasone and the other implant contained 700  $\mu$ g of dexamethasone. These single bioerodible dexamethasone (Posurdex) implants were in the same manner implanted into the vitreous of rabbit eyes (note that only one of either the 350  $\mu$ g dexamethasone or the 700  $\mu$ g dexamethasone bioerodible implant was placed in each eye) and *in vivo* vitreous concentrations of dexamethasone were monitored by vitreous sampling. The dexamethasone concentrations for each eye were measured at days 1, 4, 7, 14, 21, 28, 35, 42; as also shown by Table 4. The dexamethasone concentrations assayed (as ng dexamethasone per ml of vitreous) are set forth in Table 4 to the right of the "Day" columns.

Figure 5 shows (using the Table 4 data) the concentrations obtained (amount of dexamethasone assayed after different time periods after intra-vitreous *in vivo* implantation of the implant system of Example 6 in comparison to the release profiles obtained for the single intra-vitreous implantation of a 350  $\mu$ g or 700  $\mu$ g dexamethasone implant.

This experiment showed that particular island and sea bioerodible implants of Example 5 can release dexamethasone *in vivo* into the vitreous: (1) for a time period both much longer than (i.e. at least about 112 days vs about 30 days) and in a much more linear fashion than can a single polymer active agent implant. Significantly, this experiment

showed that the island and sea implant permitted (as a cumulative view of the release characteristics of the three implants taken together), *in vivo* over a 360 ay period, a substantially continuous release of the active agent at a substantially constant release rate (i.e. approximately linear release with substantially zero slope).

Significantly, as shown by Table 4 and Figure 5, the single polymer RG755 3 mg implant (1500  $\mu$ g dexamethasone) presented an extended release profile, thereby showing that a 75:25 (% by weight) lactide: glycolide single polymer with an inherent viscosity of about 0.50 to about 0.70 dl/g can be suitable for making an extended release implant.

Additionally, this experiment showed that the bioerodible implant system of Example 5 can release and maintain an *in vivo* in the vitreous a dexamethasone (or dexamethasone equivalent) concentration of at least 10 ng/ml or of at least about 100 ng/ml for a period of time of 120 days or for 360 days. This experiment also showed that by comparison, the single implants (350  $\mu$ g or 700  $\mu$ g of dexamethazone) exhausted delivery of dexamethasone into the vitreous after about 30 days and that even during that more shorter release period the single polymer bioerodible implant could not release or maintain a *in vivo* in the vitreous a dexamethasone (or dexamethasone equivalent) concentration with either a substantially continuous release or with a substantially constant release rate of the active agent.

25

#### Example 7

##### Treatment of an Ocular Condition with

##### An Anti-Inflammatory Active Agent Extended Release System

An extended release implant system can be used to treat an ocular condition. The implant can contain a steroid, such an anti-inflammatory steroid, such as dexamethazone as the active agent. Alternately or in addition, the active agent can be a non-steroidal anti-inflammatory, such

30

as ketoralac (available from Allergan, Irvine, California as ketoralac tromethamine ophthalmic solution, under the tradename Acular). Thus, for example, a dexamethasone or ketoralac extended release implant system of Example 1 or of Example 4 can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of, for example the dexamethazone or the ketorolac for an extended period of time to thereby treat a symptom of the ocular condition.

#### Example 8

##### Preparation and Therapeutic Use of an Anti-Angiogenesis Extended Release Implant(s)

An implant to treat an ocular condition according to the present invention can contain a steroid, such an anti-angiogenesis steroid, such as an anecortave, as the active agent. Thus, a bioerodible implant system for extended delivery of anecortave acetate (an angiostatic steroid) can be made using the method of Example 1 or the method of Example 4, but with use of anecortave acetate as the active agent, instead of dexamethasone. The implant or implants can be loaded with a



total of about 15 mg of the anecortave (i.e. 5 mg of anecortave can be loaded into each of the three implants prepared according to the Example 1 method.

5       The anecortave acetate extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an angiogenic condition or an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the  
10 following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy  
15 (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and  
20 glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the anecortave for an extended period of time to thereby treat a symptom of the ocular condition.

25

Example 9  
Preparation and Therapeutic Use of  
An Anti-VEGF Extended Release Implant(s)

VEGF (Vascular Endothelial Growth Factor) (also known as VEGF-A)  
30 is a growth factor which can stimulate vascular endothelial cell growth, survival, and proliferation. VEGF is believed to play a central role in the development of new blood vessels (angiogenesis) and the survival of immature blood vessels (vascular maintenance). Tumor expression of

VEGF can lead to the development and maintenance of a vascular network, which promotes tumor growth and metastasis. Thus, increased VEGF expression correlates with poor prognosis in many tumor types.

- 5 Inhibition of VEGF can be an anticancer therapy used alone or to complement current therapeutic modalities (eg, radiation, chemotherapy, targeted biologic therapies).

- VEGF is believed to exert its effects by binding to and activating two structurally related membrane receptor tyrosine kinases, VEGF receptor-1 (VEGFR-1 or flt-1) and VEGFR-2 (flk-1 or KDR), which are expressed  
10 by endothelial cells within the blood vessel wall. VEGF may also interact with the structurally distinct receptor neuropilin-1. Binding of VEGF to these receptors initiates a signaling cascade, resulting in effects on gene expression and cell survival, proliferation, and migration. VEGF is a member of a family of structurally related proteins (see Table A below).  
15 These proteins bind to a family of VEGFRs (VEGF receptors), thereby stimulating various biologic processes. Placental growth factor (PIGF) and VEGF-B bind primarily to VEGFR-1. PIGF modulates angiogenesis and may also play a role in the inflammatory response. VEGF-C and VEGF-D bind primarily to VEGFR-3 and stimulate lymphangiogenesis  
20 rather than angiogenesis.

Table A

VEGF Family Members	Receptors	Functions
VEGF (VEGF-A)	VEGFR-1, VEGFR-2, neuropilin-1	Angiogenesis Vascular maintenance
VEGF-B	VEGFR-1	Not established
VEGF-C	VEGF-R, VEGFR-3	Lymphangiogenesis
VEGF-D	VEGFR-2, VEGFR-3	Lymphangiogenesis
VEGF-E (viral factor)	VEGFR-2	Angiogenesis
PIGF	VEGFR-1, neuropilin-1	Angiogenesis and inflammation

An extended release bioerodible implant system can be used to treat an ocular condition mediated by a VEGF. Thus, the implant can contain as active agent a compound which acts to inhibit formation of VEGF or to inhibit the binding of VEGF to its receptor. The active agent can be, for example, ranibizumab (rhuFab V2) (Genentech, South San Francisco, California) and the implant(s) can be made using the method of Example 1 or the method of Example 4, but with use of ranibizumab as the active agent, instead of dexamethasone. Ranibizumab is an anti-VEGF (vascular endothelial growth factor) product which may have particular utility for patients with macular degeneration, including the wet form of age-related macular degeneration. The implant or implants can be loaded with a total of about 300-500  $\mu$ g of the ranibizumab (i.e. about 150  $\mu$ g of ranibizumab can be loaded into each of the three implants prepared according to the Example 1 method.

15

The ranibizumab extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of

30

the ranibizumab for an extended period of time to thereby treat a symptom of the ocular condition.

Pegaptanib is an aptamer that can selectively bind to and neutralize VEGF and may have utility for treatment of, for example, age-related macular degeneration and diabetic macular edema by inhibiting abnormal blood vessel growth and by stabilizing or reverse blood vessel leakage in the back of the eye resulting in improved vision. A bioerodible implant system for extended delivery of pegaptanib sodium (Macugen; Pfizer Inc, New York or Eyetech Pharmaceuticals, New York) can also be made using the method of Example 1 or the method of Example 4, but with use of pegaptanib sodium as the active agent, instead of dexamethasone. The implant or implants can be loaded with a total of about 1 mg to 3 mg of Macugen according to the Example 1 method.

The pegaptanib sodium extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect.

20

An extended release bioerodible intraocular implant for treating an ocular condition, such as an ocular tumor can also be made as set forth in this Example 9, using about 1-3 mg of the VEGF Trap compound available from Regeneron, Tarrytown, new York.

25

#### Example 10 Preparation and Therapeutic Use of Beta Blocker Extended Release Implant(s)

An extended release implant system to treat an ocular condition can contain a beta-adrenergic receptor antagonist (i.e. a "beta blocker) such as levobunolol, betaxolol, carteolol, timolol hemihydrate and timolol. Timolol maleate is commonly used to treat of open-angle glaucoma. Thus, an extended release bioerodible implant system containing timolol

30

maleate (available from multiple different suppliers under the trade names Timoptic, Timopol or Loptomit) as the active agent can be made using the method of Example 1 or the method of Example 4, but with use of timolol maleate instead of dexamethasone. Thus, about 50  $\mu\text{g}$  to 150  $\mu\text{g}$  of the timolol maleate can be loaded into each of the three implants prepared according to the Example 1 method.

The timolol extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the timolol for an extended period of time to thereby treat a symptom of the ocular condition by, for example, causing an intra-ocular pressure depression

#### Example 11

##### Preparation and Therapeutic Use of Prostamide Extended Release Implant(s)

An extended release implant system can be used to treat an ocular condition can contain a prostamide. Prostamides are naturally occurring

substances biosynthesized from anandamide in a pathway that includes COX2. Bimatoprost (Lumigan) is a synthetic prostamide analog chemically related to prostamide F. Lumigan has been approved by the FDA for the reduction of elevated intraocular pressure (IOP) in patients  
5 with open-angle glaucoma or ocular hypertension who are intolerant of or insufficiently responsive to other IOP-lowering medications. Lumigan is believed to lower intraocular pressure by increasing the outflow of aqueous humor.

10 Thus, an extended release bioerodible implant system containing Lumigan (Allergan, Irvine, California) as the active agent can be made using the method of Example 1 or the method of Example 4, but with use of timolol maleate instead of dexamethasone. Thus, about 100  $\mu$ g to 300  $\mu$ g of Lumigan can be loaded into each of the three implants  
15 prepared according to the Example 1 method.

The Lumigan extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be  
20 an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema  
25 (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior  
30 ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in

Example 2 and 6. The implant(s) can release a therapeutic amount of the Lumigan for an extended period of time to thereby treat a symptom of the ocular condition by, for example, causing an intra-ocular pressure depression

5

Example 12  
Preparation and Therapeutic Use of  
An Alpha-2 Extended Release Implant(s)

An extended release implant system can be used to treat an ocular condition wherein the implant contains as the active agent an alpha-2 adrenergic receptor agonist, such as clonidine, apraclonidine, or brimonidine. Thus, an extended release bioerodible implant system containing brimonidine (Allergan, Irvine, California, as Alphagan or Alphagan P) as the active agent can be made using the method of Example 1 or the method of Example 4, but with use of Alphagan instead of dexamethasone. Thus, about 50  $\mu$ g to 100  $\mu$ g of Alphagan can be loaded into each of the three implants prepared according to the Example 1 method.

The brimonidine extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction,

retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the brimonidine for an extended period of time to thereby treat a  
5 symptom of the ocular condition by, for example, causing an intra-ocular pressure depression

Example 13  
Preparation and Therapeutic Use of  
10 a Retinoid Extended Release Implant(s)

An extended release implant system can be used to treat an ocular condition. The implant can contain a retinoid such as an ethyl nicotinate, such as a tazarotene. Thus, an extended release bioerodible implant system containing tazarotene (Allergan, Irvine, California) as the active  
15 agent can be made using the method of Example 1 or the method of Example 4, but with use of tazarotene instead of dexamethasone. Thus, about 100  $\mu$ g to 500  $\mu$ g of tazarotene can be loaded into each of the three implants prepared according to the Example 1 method.

20 The tazarotene extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular  
25 degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic  
30 retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction,



retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the tazarotene for an extended period of time to thereby treat a symptom of the ocular condition by, for example, causing an intra-ocular pressure depression

#### Example 14

Preparation and Therapeutic Use of  
a Tyrosine Kinase Inhibitor Extended Release Implant(s)

Generally, tyrosine kinase inhibitors are small molecule inhibitors of growth factor signaling. Protein tyrosine kinases (PTKs) comprise a large and diverse class of proteins having enzymatic activity. The PTKs play an important role in the control of cell growth and differentiation. For example, receptor tyrosine kinase mediated signal transduction is initiated by extracellular interaction with a specific growth factor (ligand), followed by receptor dimerization, transient stimulation of the intrinsic protein tyrosine kinase activity and phosphorylation. Binding sites are thereby created for intracellular signal transduction molecules and lead to the formation of complexes with a spectrum of cytoplasmic signaling molecules that facilitate the appropriate cellular response (e.g., cell division, metabolic homeostasis, and responses to the extracellular microenvironment).

With respect to receptor tyrosine kinases, it has been shown also that tyrosine phosphorylation sites function as high-affinity binding sites for SH2 (src homology) domains of signaling molecules. Several intracellular substrate proteins that associate with receptor tyrosine kinases (RTKs) have been identified. They may be divided into two principal groups: (1) substrates which have a catalytic domain; and (2) substrates which lack such domain but serve as adapters and associate with catalytically active molecules. The specificity of the interactions between receptors or proteins and SH2 domains of their substrates is

determined by the amino acid residues immediately surrounding the phosphorylated tyrosine residue. Differences in the binding affinities between SH2 domains and the amino acid sequences surrounding the phosphotyrosine residues on particular receptors are consistent with the  
5 observed differences in their substrate phosphorylation profiles. These observations suggest that the function of each receptor tyrosine kinase is determined not only by its pattern of expression and ligand availability but also by the array of downstream signal transduction pathways that are activated by a particular receptor. Thus, phosphorylation provides  
10 an important regulatory step which determines the selectivity of signaling pathways recruited by specific growth factor receptors, as well as differentiation factor receptors.

Aberrant expression or mutations in the PTKs have been shown to  
15 lead to either uncontrolled cell proliferation (e.g. malignant tumor growth) or to defects in key developmental processes. Consequently, the biomedical community has expended significant resources to discover the specific biological role of members of the PTK family, their function in differentiation processes, their involvement in tumorigenesis and in other  
20 diseases, the biochemical mechanisms underlying their signal transduction pathways activated upon ligand stimulation and the development of novel drugs.

Tyrosine kinases can be of the receptor-type (having extracellular,  
25 transmembrane and intracellular domains) or the non-receptor type (being wholly intracellular). The RTKs comprise a large family of transmembrane receptors with diverse biological activities. The intrinsic function of RTKs is activated upon ligand binding, which results in phosphorylation of the receptor and multiple cellular substrates, and  
30 subsequently in a variety of cellular responses.

At present, at least nineteen (19) distinct RTK subfamilies have been identified. One RTK subfamily, designated the HER subfamily, is believed to be comprised of EGFR, HER2, HER3 and HER4. Ligands to the Her subfamily of receptors include epithelial growth factor (EGF),  
5 TGF- $\alpha$ , amphiregulin, HB-EGF, betacellulin and heregulin.

A second family of RTKs, designated the insulin subfamily, is comprised of the INS-R, the IGF-1R and the IR-R. A third family, the "PDGF" subfamily includes the PDGF  $\alpha$  and  $\beta$  receptors, CSFIR, c-kit  
10 and FLK-II. Another subfamily of RTKs, identified as the FLK family, is believed to be comprised of the Kinase insert Domain-Receptor fetal liver kinase-1 (KDR/FLK-1), the fetal liver kinase 4 (FLK-4) and the fms-like tyrosine kinase 1 (flt-1). Each of these receptors was initially believed to be receptors for hematopoietic growth factors. Two other  
15 subfamilies of RTKs have been designated as the FGF receptor family (FGFR1, FGFR2, FGFR3 and FGFR4) and the Met subfamily (c-met and Ron).

Because of the similarities between the PDGF and FLK subfamilies,  
20 the two subfamilies are often considered together. The known RTK subfamilies are identified in Plowman et al, 1994, DN&P 7(6): 334-339, which is incorporated herein by reference.

The non-receptor tyrosine kinases represent a collection of cellular  
25 enzymes which lack extracellular and transmembrane sequences. At present, over twenty-four individual non-receptor tyrosine kinases, comprising eleven (11) subfamilies (Src, Frk, Btk, Csk, Abl, Zap70, Fes/Fps, Fak, Jak, Ack and LIMK) have been identified. At present, the Src subfamily of non-receptor tyrosine kinases is comprised of the  
30 largest number of PTKs and include Src, Yes, Fyn, Lyn, Lck, Blk, Hck, Fgr and Yrk. The Src subfamily of enzymes has been linked to oncogenesis. A more detailed discussion of non-receptor tyrosine

kinases is provided in Bolen, 1993, Oncogen 8: 2025-2031, which is incorporated herein by reference.

Many of the tyrosine kinases, whether an RTK or non-receptor  
5 tyrosine kinase, have been found to be involved in cellular signaling  
pathways leading to cellular signal cascades leading to pathogenic  
conditions, including cancer, psoriasis and hyper immune response.

In view of the surmised importance of PTKs to the control, regulation  
10 and modulation of cell proliferation the diseases and disorders  
associated with abnormal cell proliferation, many attempts have been  
made to identify receptor and non-receptor tyrosine kinase "inhibitors"  
using a variety of approaches, including the use of mutant ligands (U.S.  
Patent No. 4,966,849), soluble receptors and antibodies (PCT  
15 Application No. WO 94/10202; Kendall & Thomas, 1994, Proc. Nat'l  
Acad. Sci 90: 10705-09; Kim, et al, 1993, Nature 362: 841-844), RNA  
ligands (Jellinek, et al, Biochemistry 33: 10450-56); Takano, et al, 1993,  
Mol. Bio. Cell 4:358A; Kinsella, et al, 1992, Exp. Cell Res. 199: 56-62;  
Wright, et al, 1992, J. Cellular Phys. 152: 448-57) and tyrosine kinase  
20 inhibitors (PCT Application Nos. WO 94/03427; WO 92/21660; WO  
91/15495; WO 94/14808; U.S. Patent No. 5,330,992; Mariani, et al,  
1994, Proc. Am. Assoc. Cancer Res. 35: 2268).

An extended release implant system can be used to treat an ocular  
25 condition wherein the implant contains a tyrosine kinase inhibitor (TKI)  
such as a TKI set forth in published U.S. patent application 2004  
00019098 (available from Allergan, Irvine, California) as the active agent  
can be made using the method of Example 1 or the method of Example  
4, but with use of a TKI instead of dexamethasone. Thus, about 100  $\mu$ g  
30 to 300  $\mu$ g of a TKI can be loaded into each of the three implants  
prepared according to the Example 1 method.

The TKI extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the TKI for an extended period of time to thereby treat a symptom of the ocular condition by, for example, causing an intra-ocular pressure depression.

Example 15  
Preparation and Therapeutic Use of  
an NMDA Antagonist Extended Release Implant(s)

It is believed that overstimulation of the *N*-methyl-D-aspartate (NMDA) receptor by glutamate is implicated in a variety of disorders. Memantine is an NMDA antagonist which can be used to reduce neuronal damage mediated by the NMDA receptor complex. Memantine is a available form Merz Pharmaceuticals, Greensboro, North Carolina under the trade name Axura. An extended release implant system can be used to treat an ocular condition. The implant can contain an NMDA antagonist such as memantine. Thus, an extended release bioerodible

implant system containing memantine as the active agent can be made using the method of Example 1 or the method of Example 4, but with use of memantine instead of dexamethasone. Thus, about 400  $\mu$ g to 700  $\mu$ g of memantine can be loaded into each of the three implants  
5 prepared according to the Example 1 method.

The memantine extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition  
10 can be an inflammatory condition such as uveitis or the patient can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema  
15 (including cystoid macular edema and diabetic macular edema); Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior  
20 ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the memantine for an extended period of time to thereby treat a  
25 symptom of the ocular condition.

#### Example 16

##### Preparation and Therapeutic Use of an Estratropone Extended Release Implant(s)

30 Certain estratropones have anti-angiogenesis, anti-neoplastic and related useful therapeutic activities. An extended release implant system can be used to treat an ocular condition. The implant can contain an estratropone such as 2-methoxyestradiol (available form

Entremed, Inc., of Rockville, Maryland under the tradename Panzem).

Thus, an extended release bioerodible implant system containing memantine as the active agent can be made using the method of Example 1 or the method of Example 4, but with use of 2-

5 methoxyestradiol instead of dexamethasone. 2-methoxyestradiol can be used as a small molecule angiogenic inhibitor to block abnormal blood vessel formation in the back of the eye. Thus, about 400  $\mu$ g to 700  $\mu$ g of 2-methoxyestradiol can be loaded into each of the three implants prepared according to the Example 1 method.

10

The 2-methoxyestradiol extended release implant system can be implanted into an ocular region or site (i.e. into the vitreous) of a patient with an ocular condition for a desired therapeutic effect. The ocular condition can be an inflammatory condition such as uveitis or the patient  
15 can be afflicted with one or more of the following afflictions: macular degeneration (including non-exudative age related macular degeneration and exudative age related macular degeneration); choroidal neovascularization; acute macular neuroretinopathy; macular edema (including cystoid macular edema and diabetic macular edema);  
20 Behcet's disease, diabetic retinopathy (including proliferative diabetic retinopathy); retinal arterial occlusive disease; central retinal vein occlusion; uveitic retinal disease; retinal detachment; retinopathy; an epiretinal membrane disorder; branch retinal vein occlusion; anterior ischemic optic neuropathy; non-retinopathy diabetic retinal dysfunction,  
25 retinitis pigmentosa and glaucoma. The implant(s) can be inserted into the vitreous using the procedure (trocar implantation) set forth in Example 2 and 6. The implant(s) can release a therapeutic amount of the 2-methoxyestradiol for an extended period of time to thereby treat a symptom of the ocular condition.

30

Using the same methodology, additional extended release single or multiple polymer implants can be prepared wherein the active agent is,

for example, an agent to treat intravitreal hemorrhage (such as Vitrase, available from Ista Pharmaceuticals ), an antibiotic (such as cyclosporine, or gatifloxacin, the former being available from Allergan, Irvine, California under the tradename Restasis and the later from  
5 Allergan under the tradename Zymar), ofloxacin, an androgen, epinastine (Elestat, Allergan, Irvine, CA), or with a combination of two or more active agents (such as a combination in a single extended release implant of a prostamide (i.e. brimatoprost) and a beta blocker (i.e. timolol) or a combination of an alpha 2 adrenergic agonist (i.e.  
10 brimonidine) and a beta blocker, such as timolol) in the same extended delivery system. An implant within the scope of the present invention can be used in conjunction with a photodynamic therapy or laser procedure upon an eye tissue.

15 All references, articles, patents, applications and publications set forth above are incorporated herein by reference in their entireties.

Accordingly, the spirit and scope of the following claims should not be limited to the descriptions of the preferred embodiments set forth above



We claim:

1. A drug delivery system for treating an ocular condition, the  
5 drug delivery system comprising:
  - (a) at least one bioerodible implant suitable for insertion into an ocular region or site, the bioerodible implant comprising:
    - (i) an active agent, and;
    - (ii) a bioerodible polymer,  
10 wherein the bioerodible implant can release a therapeutic level of the active agent into the ocular region or site for a period time between about 30 days and about 1 year.
2. The drug delivery system of claim 1, wherein the active agent  
15 is an anti-inflammatory agent.
3. The drug delivery system of claim 1, wherein the bioerodible polymer is a PLGA co-polymer.
- 20 4. The drug delivery system of claim 1, wherein the bioerodible implant has a weight between about 1  $\mu$ g and about 100 mg.
5. The drug delivery system of claim 1, wherein the bioerodible implant has no dimension less than about 0.1 mm and no dimension  
25 greater than about 20 mm.
6. The drug delivery system of claim 1, wherein the drug delivery system comprises a plurality of bioerodible implants.
- 30 7. The drug delivery system of claim 1, wherein the active agent is substantially homogenously dispersed within the bioerodible polymer.

8. The drug delivery system of claim 1, wherein the active agent is associated with the bioerodible polymer in the form of particles of active agent and bioerodible polymer.

5           9. The drug delivery system of claim 1, wherein the drug delivery system comprises: (a) a portion of the active agent substantially homogenously dispersed within a portion of the bioerodible polymer, and;

             (b) a portion of the same or of a different active agent associated  
10 with a portion of same or of a different bioerodible polymer in the form of particles of active agent and the bioerodible polymer.

10. A drug delivery system for treating an ocular condition, the drug delivery system comprising:

15           (a) a bioerodible implant suitable for insertion into an ocular region or site, the bioerodible implant comprising;

             (i) an active agent, and;

             (ii) a bioerodible polymer,

             wherein the bioerodible implant can release a therapeutic level of  
20 the active agent upon insertion into a posterior ocular region or site for a period time of at least about 40 days.

11. A drug delivery system for treating an ocular condition, the drug delivery system comprising:

25           (a) a plurality of bioerodible implants implantable in a posterior ocular region or site, each implant comprising;

             (i) an active agent, and;

             (ii) a bioerodible polymer,

             wherein the plurality of bioerodible implants can substantially  
30 continuously release *in vivo* a therapeutic level of the active agent for a period time between about 5 days and about 1 year.

12. The drug delivery system of claim 11, wherein the drug delivery system comprises:

- (a) a first implant with a first release characteristic, and;
- (b) a second implant with a second release characteristic,

5 wherein the first and second release characteristics differ.

13. The drug delivery system of claim 12, wherein the release profile of the drug delivery system corresponds to the sum of the first and second release profiles.

10

14. The drug delivery system of claim 11, wherein the drug delivery system comprises:

- (a) a first implant with a first release characteristic,
- (b) a second implant with a second release characteristic, and;
- (c) a third implant with a third release characteristic.

15

15. The drug delivery system of claim 14, wherein the release profile of the drug delivery system corresponds to the sum of the first, second and third release profiles.

20

16. The drug delivery system of claim 11, wherein the drug delivery system comprises at least two different implants which have different bioerodible polymers.

25 17. The drug delivery system of claim 14 comprising first, second and third bioerodible implants, wherein

the first implant comprises a first polymer with a first average molecular weight; the second implant comprises a second polymer with a second average molecular weight, and

30 the third implant comprises a third polymer with a third average molecular weight.

18. The drug delivery system of claim 11, wherein the active agent is an anti-inflammatory compound.

19. The drug delivery system of claim 11, wherein the active  
5 agent is an anti-angiogenesis compound.

20. A drug delivery system for treating an ocular condition comprising;

(a) a plurality of bioerodible implants implantable in a posterior  
10 ocular region, each implant comprising

(i) an anti-inflammatory drug, and;

(ii) a bioerodible polymer,

wherein the plurality of bioerodible implants can substantially continuously release the anti-inflammatory drug at a level of at least  
15 about a 10 ng/ml dexamethasone equivalent for a period of between 5 days and 1 year.

21. An extended release bioerodible implant for treating an ocular condition, the bioerodible implant being made by:

20 (a) blending an active agent and a first bioerodible polymer to form a first solid material;

(b) breaking the first solid material into particles;

(c) blending the particles with the active agent and a second bioerodible polymer, to thereby form a bioerodible implant, wherein the  
25 bioerodible implant can release a therapeutic level of the active agent at a substantially continuous rate for a period time between about 50 days and about 1 year.

22. A bioerodible implant for treating an ocular condition, the  
30 bioerodible implant being made by:

(a) blending a steroidal anti-inflammatory drug and a first bioerodible polymer to form a first solid material;

(b) breaking the solid material into particles;

(c) blending the particles with the steroidal anti-inflammatory drug and a second bioerodible polymer to form a bioerodible implant, wherein the bioerodible implant can release a therapeutic level of the active agent at a substantially continuous rate for a period time between about 50 days and about 1 year.

23. The bioerodible implant of claim 22 wherein the implant can substantially continuously release the steroidal anti-inflammatory drug at a dexamethasone equivalent level corresponding to at least 10 ng/ml for a period of at between 50 days and one year.

24. The bioerodible implant of claim 22 wherein the implant can continuously release the steroidal anti-inflammatory drug at a dexamethasone equivalent corresponding to at least 50 ng/ml for a period of at least about 50 days.

25. A bioerodible implant for treating an ocular condition, comprising:

(a) a dispersion comprising an active agent dispersed with a first bioerodible polymer,

(b) a particle comprising the active agent and a second bioerodible polymer,

wherein the particle has an active agent release characteristic which differs from the active agent release characteristic of the dispersion.

26. The bioerodible implant of claim 25 wherein the implant can substantially continuously release the active agent at a level corresponding to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

27. The bioerodible implant of claim 25 wherein the implant can substantially continuously release the active agent at a level corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

5

28. A bioerodible implant for treating an inflammation-mediated condition of the eye, the implant being made by:

(a) blending a first active agent and a first bioerodible polymer to thereby form a first active agent polymer mixture;

10 (b) blending a second active agent and a second bioerodible polymer to thereby form a second active agent polymer mixture;

(c) co-extruding the first and second active agent polymer mixtures to thereby form a bioerodible implant containing first and second regions, the first region containing the first active agent polymer mixture, and the second region containing the second active agent polymer mixture, wherein first and second regions have different active agent release characteristics.

20 29. The bioerodible implant of claim 28, wherein the first active agent and the second active agent are the same active agent.

30. The bioerodible implant of claim 28, wherein the first active agent and the second active agent are different active agents.

25 31. The bioerodible implant of claim 28, wherein the first polymer and the second polymer are the same polymer.

32. The bioerodible implant of claim 28, wherein the first polymer and the second polymer are different polymers.

30

33. The bioerodible implant of claim 28 wherein the implant can substantially continuously releases active agent at levels corresponding

to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

34. The bioerodible implant of claim 28 wherein the implant can  
5 substantially continuously releases active agent at levels corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for a period of at least about 50 days.

35. A bioerodible implant for treating a posterior ocular condition,  
10 bioerodible implant being made by:

(a) blending a first active agent and a first bioerodible polymer to thereby form a first active agent polymer mixture;

(b) co-extruding the first active agent polymer mixture with a  
second polymer to thereby form a bioerodible implant containing first  
15 and second regions, the first region containing the first active agent polymer mixture, and the second region containing the second polymer mixture.

36. The bioerodible implant of claim 35, wherein where the first  
20 polymer and the second polymer are the same polymer.

37. The bioerodible implant of claim 35, wherein the first polymer and the second polymer are different polymers.

25 38. A bioerodible implant for treating a posterior ocular condition, the bioerodible implant comprising:

(a) a first region containing a first mixture of an active agent and a first bioerodible polymer, and;

(b) a second region containing a second mixture of the active  
30 agent and a second bioerodible polymer,

wherein the first and second regions have different active agent release characteristics.

39. The bioerodible implant of claim 38 wherein the implant can substantially continuously releases active agent at levels corresponding to at least 10 ng/ml of dexamethasone or dexamethasone equivalent for  
5 a period of at least about 50 days.

40. The bioerodible implant of claim 38 wherein the implant can substantially continuously releases active agent at levels corresponding to at least 50 ng/ml of dexamethasone or dexamethasone equivalent for  
10 a period of at least about 50 days.

41. A method for treating an ocular condition, the method comprising implanting into an ocular region or site a drug delivery system comprising:

15 (a) at least one bioerodible implant suitable for insertion into an ocular region or site, the bioerodible implant comprising;

(i) an active agent, and;

(ii) a bioerodible polymer,

wherein the bioerodible implant can release a therapeutic level of  
20 the active agent at a substantially continuous rate upon insertion into an ocular region or site for a period time between about 50 days and about 1 year.






Figure 1B




Figure 2




Figure 3




Figure 4





Figure 5



## INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/US2005/013143

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 7 A61K9/00 A61K31/57 A61P27/02		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 7 A61K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, PAJ, WPI Data, BIOSIS, EMBASE		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 331 313 B1 (WONG VERNON G ET AL) 18 December 2001 (2001-12-18)  claims 1-10,18 figures 1-5 column 9, line 60 - column 10, line 5 column 10, line 46 - column 12, line 19 page 14, line 10 - page 14, line 43 examples 7-9	1,2,4,5, 7,8,10, 28,31, 35,36,41
X	US 4 304 765 A (SHELL ET AL) 8 December 1981 (1981-12-08)  claims 1-12 column 11, line 20 - column 11, line 40 column 5, line 44 - column 5, line 45 ----- -/--	1,2,4,5, 7,8,10, 28,31, 35,36,41
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
15 July 2005		28/07/2005
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  Schifferer, H

## INTERNATIONAL SEARCH REPORT

Intern: 1 Application No  
PCT/US2005/013143

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02/43785 A (OCULEX PHARMACEUTICALS, INC; WONG, VERNON, G) 6 June 2002 (2002-06-06)  claims 1-45 examples 1,2,5 paragraph '0023! - paragraph '0041! paragraphs '0047! - '0052! -----	1-5,7,8, 10,28, 31,35, 36,41
X	US 6 306 426 B1 (OLEJNIK OREST ET AL) 23 October 2001 (2001-10-23)  claims 1-10 figure 8 column 5, line 10 - column 8, line 60 -----	1,2,4,5, 7,8,10, 28,31, 35,36,41
X	US 5 869 079 A (WONG ET AL) 9 February 1999 (1999-02-09)  claim 1 figures 1-3 examples 1,2 column 2, line 27 - column 7, line 65 -----	1-5,7,8, 10,28, 31,35, 36,41
X	KUNOU N ET AL: "BIODEGRADABLE SCLERAL IMPLANT FOR CONTROLLED INTRAOCULAR DELIVERY OF BETAMETHASONE PHOSPHATE" JOURNAL OF BIOMEDICAL MATERIALS RESEARCH, WILEY, NEW YORK, NY, US, vol. 51, no. 4, 2000, pages 635-641, XP001205588 ISSN: 0021-9304 abstract page 641, left-hand column, line 18 - page 641, left-hand column, line 30 page 636, left-hand column, line 28 - page 637, right-hand column, line 21 -----	1-5,7,8, 10,28, 31,35, 36,41
P,X	WO 2004/062649 A (ALLERGAN, INC) 29 July 2004 (2004-07-29)  claims 1-89 examples 1,2,7 paragraph '0041! - paragraph '0049! paragraph '0059! - paragraph '0087! ----- -/--	1-5,7,8, 10,28, 31,35, 36,41



## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US2005/013143

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	<p>EP 1 550 471 A (ALLERGAN INC) 6 July 2005 (2005-07-06)</p> <p>paragraph '0046! - paragraph '0058! paragraph '0060! examples 1,5 claims 1-12</p> <p>-----</p>	<p>1-5,7,8, 10,28, 31,35, 36,41</p>

## INTERNATIONAL SEARCH REPORT

In: International application No.  
PCT/US2005/013143

### Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.: 41 (in part)  
because they relate to subject matter not required to be searched by this Authority, namely:  
Although claim 41 is directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the compound/composition.
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

### Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.  
☐ No protest accompanied the payment of additional search fees.

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern Application No  
PCT/US2005/013143

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6331313	B1	18-12-2001	AU 1218701 A	08-05-2001
			BR 0007454 A	30-10-2001
			CA 2355313 A1	03-05-2001
			CN 1360497 A	24-07-2002
			EP 1143935 A2	17-10-2001
			JP 2003512417 T	02-04-2003
			NO 20013094 A	22-08-2001
			WO 0130323 A2	03-05-2001
US 4304765	A	08-12-1981	NONE	
WO 0243785	A	06-06-2002	AU 3649502 A	11-06-2002
			BR 0115772 A	13-01-2004
			CA 2429998 A1	06-06-2002
			EP 1339438 A2	03-09-2003
			EP 1550471 A1	06-07-2005
			JP 2004514702 T	20-05-2004
			JP 2004210798 A	29-07-2004
			WO 0243785 A2	06-06-2002
			US 2004137034 A1	15-07-2004
			US 2002182185 A1	05-12-2002
US 6306426	B1	23-10-2001	US 6110485 A	29-08-2000
			US 6074661 A	13-06-2000
			US 2005142165 A1	30-06-2005
			US 2003185875 A1	02-10-2003
			US 2004219187 A1	04-11-2004
			US 6455062 B1	24-09-2002
			US 2002022047 A1	21-02-2002
			AU 738338 B2	13-09-2001
			AU 8777798 A	01-03-1999
			CA 2300154 A1	18-02-1999
			DE 69827138 D1	25-11-2004
			EP 1003569 A2	31-05-2000
			ES 2232005 T3	16-05-2005
			HK 1026377 A1	06-05-2005
			JP 2001513369 T	04-09-2001
			WO 9907418 A2	18-02-1999
US 5869079	A	09-02-1999	AU 721421 B2	06-07-2000
			AU 5962496 A	18-12-1996
			BR 9608642 A	24-08-1999
			CA 2222889 A1	05-12-1996
			CN 1191492 A	26-08-1998
			EP 1477187 A1	17-11-2004
			EP 0831912 A1	01-04-1998
			JP 11506450 T	08-06-1999
			PL 323747 A1	14-04-1998
			RU 2175561 C2	10-11-2001
			TW 487580 B	21-05-2002
			WO 9638174 A1	05-12-1996
			US 6369116 B1	09-04-2002
			US 2003095995 A1	22-05-2003
			US 2005048098 A1	03-03-2005
WO 2004062649	A	29-07-2004	US 2004137059 A1	15-07-2004
			US 2005048099 A1	03-03-2005
			WO 2004062649 A2	29-07-2004

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter Application No  
PCT/US2005/013143

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1550471 A	06-07-2005	EP 1550471 A1	06-07-2005
		AU 3649502 A	11-06-2002
		BR 0115772 A	13-01-2004
		CA 2429998 A1	06-06-2002
		EP 1339438 A2	03-09-2003
		JP 2004514702 T	20-05-2004
		JP 2004210798 A	29-07-2004
		WO 0243785 A2	06-06-2002
		US 2004137034 A1	15-07-2004
		US 2002182185 A1	05-12-2002